



ENVIRONMENTAL SAFETY & HYGIENE ASSOCIATES, INC.

- Indoor Air Quality
- OSHA Compliance
- Asbestos Consulting
- Training
- Lead Consulting
- Industrial Hygiene

August 15, 2007

Wally Geyer
Casco Bay Ventures
130 Eastern Promenade
Portland Maine 04101

Re: Asbestos Bulk Sampling Results at 130 Eastern Promenade, Portland Maine.

Dear Mr. Geyer:

Environmental Safety & Hygiene Associates Inc. (ESHA) is providing you with the asbestos bulk testing results for the 103 samples collected from various interior and exterior locations. ESHA conducted the survey on August 2, 2007.

The bulk samples were collected with standard sampling protocols, properly packaged and shipped to EMSL Analytical Laboratory, Westmont, New Jersey for analysis by Polarized Light Microscopy (PLM) specific to asbestos content by volume.

The bulk sample analysis indicates that the following materials contain asbestos:

Unit #1

- Kitchen Linoleum- **10 % Chrysotile Asbestos**

Unit #2

- Bathroom 9"x 9" Floor tiles - **5 % Chrysotile Asbestos**

Unit #7

- Living Room 12"x 12" Floor tiles - **5 % Chrysotile Asbestos**

Unit #10

- Bathroom Linoleum - **10% Chrysotile Asbestos**

Page 2

**130 Eastern Promenade
Portland Maine.**

Unit #11

- Hall & Bathroom Linoleum - **10% Chrysotile Asbestos**

Attic


- Blown insulation – **Less Than 0.25% Chrysotile Asbestos**

Any suspect materials with greater than 1% asbestos by volume are State of Maine DEP regulated asbestos materials. Any suspect materials with Less than 1% asbestos by volume is an OSHA regulated material.

The asbestos materials will need to be removed by a State of Maine DEP licensed abatement contractor prior to any renovations or demolitions.

We appreciate the opportunity to service your asbestos testing needs, should you require further bulk or air quality sampling please feel free to contact us at any time.

Very truly,



Mark Griffeth

Asbestos Inspector AI-0230

ASBESTOS BULK SAMPLE REPORT

Prepared for:

Casco Bay Ventures
130 Eastern Prom.
Portland, ME 04101

Project # 07-178 – 130 Eastern Prom. Portland

Testing Date:

August 08, 2007

Prepared by

Environmental Safety & Hygiene Associates, Inc.
5 Delta Drive
Westbrook, ME 04092
Ph: 207-854-2711 Fax: 207-854-2609

SAMPLE NUMBER	LOCATION AREA	SAMPLE DESCRIPTION / COLOR	% ASBESTOS
B-1A - Tile	Unit #1 Kitchen	12 x 12 Floor Tile - Gray/Tan	None Detected
B-1A - Mastic	"	Floor Tile Mastic - Clear	None Detected
B-1B - Tile	"	12 x 12 Floor Tile - Gray/Tan	None Detected
B-1B - Mastic	"	Floor Tile Mastic - Clear	None Detected
B-1C - Tile	"	12 x 12 Floor Tile - Gray/Tan	None Detected
B-1C - Mastic	"	Floor Tile Mastic - Clear	None Detected
B-2A - Lino	Unit #1 Kitchen	Linoleum - Tan/White	10% Chrysotile
B-2A - Mastic	"	Mastic - Brown	None Detected
B-2B - Lino	"	Linoleum - Tan/White	Stop Positive (Not Analyzed)
B-2B - Mastic	"	Mastic - Brown	None Detected
B-2C - Lino	"	Linoleum - Tan/White	Stop Positive (Not Analyzed)
B-2C - Mastic	"	Mastic - Brown	<i>Insufficient Material</i>
B-3A	Unit #1 Closet - Tan	Linoleum - Various	None Detected
B-3B	"	"	None Detected
B-3C	"	"	None Detected
B-4A	Unit #1 Closet - Brown	Linoleum - Various	None Detected
B-4B	"	"	None Detected
B-4C	"	"	None Detected
B-5A	Unit #1 Living Room	1 x 1 Ceiling Tile (Pin hole) - Brown/White	None Detected
B-5B	"	"	None Detected
B-5C	"	"	None Detected
B-6A	Unit #1 Dining Room	1 x 1 Ceiling Tile (Textured) - Brown/White	None Detected
B-6B	"	"	None Detected
B-6C	"	"	None Detected
B-7A	Unit #1 Bed Room	1 x 1 Ceiling Tile (Smooth) - Brown/White	None Detected
B-7B	"	"	None Detected
B-7C	"	"	None Detected

SAMPLE NUMBER	LOCATION AREA	SAMPLE DESCRIPTION / COLOR	% ASBESTOS
B-8A - Tile	Unit #2 Bathroom	9 x 9 Floor Tile - Brown	5% Chrysotile
B-8A - Mastic	"	Floor Tile Mastic - Brown/Black	None Detected
B-8B - Tile	"	9 x 9 Floor Tile - Brown	Stop Positive (Not Analyzed)
B-8B - Mastic	"	Floor Tile Mastic - Brown/Black	None Detected
B-8C - Tile	"	9 x 9 Floor Tile - Brown	Stop Positive (Not Analyzed)
B-8C - Mastic	"	Floor Tile Mastic - Brown/Black	None Detected
B-9A - Tile	Unit #4 Bathroom	12 x 12 Floor Tile over 9 x 9 Floor Tile - Tan/White	None Detected
B-9A - Mastic	"	Mastic - Brown	None Detected
B-9B - Tile	"	12 x 12 Floor Tile over 9 x 9 Floor Tile - Tan/White	None Detected
B-9B - Mastic	"	Mastic - Brown	None Detected
B-9C - Tile	"	12 x 12 Floor Tile over 9 x 9 Floor Tile - Tan/White	None Detected
B-9C - Mastic	"	Mastic - Brown	None Detected
B-10A	Unit #6 Green Bathroom	9 x 9 Floor Tile - Various	None Detected
B-10B	"	"	None Detected
B-10C	"	"	None Detected
B-11A	Unit #6 Pantry	Linoleum - Various	None Detected
B-11B	"	"	None Detected
B-11C	"	"	None Detected
B-12A - Tile	Unit #7	Linoleum - Brown/White	None Detected
B-12A - Mastic	"	Mastic - Brown	None Detected
B-12B - Tile	"	Linoleum - Brown/White	None Detected
B-12B - Mastic	"	Mastic - Brown	None Detected
B-12C - Tile	"	Linoleum - Brown/White	None Detected
B-12C - Mastic	"	Mastic - Brown	None Detected
B-13A - Tile	Unit #7 Living Room	12 x 12 Floor Tile - Brown/White	5% Chrysotile
B-13A - Mastic	"	Mastic - Brown	None Detected
B-13B - Tile	"	12 x 12 Floor Tile - Brown/White	Stop Positive (Not Analyzed)
B-13B - Mastic	"	Mastic - Brown	None Detected
B-13C - Tile	"	12 x 12 Floor Tile - Brown/White	Stop Positive (Not Analyzed)
B-13C - Mastic	"	Mastic - Brown	None Detected

SAMPLE NUMBER	LOCATION AREA	SAMPLE DESCRIPTION / COLOR	% ASBESTOS
B-14A	Unit #7 Living Room & Bed Room	2 x 4 Ceiling Tiles - Brown/White	None Detected
B-14B	"	"	None Detected
B-14C	"	"	None Detected
B-15A	Unit #8 Closet	Linoleum - Various	None Detected
B-15B	"	"	None Detected
B-15C	"	"	None Detected
B-16A - Tile	Unit #8 Bathroom	12 x 12 Floor Tile - Gray/White	None Detected
B-16A - Mastic	"	Mastic - Clear	None Detected
B-16B - Tile	"	12 x 12 Floor Tile - Gray/White	None Detected
B-16B - Mastic	"	Mastic - Clear	None Detected
B-16C - Tile	"	12 x 12 Floor Tile - Gray/White	None Detected
B-16C - Mastic	"	Mastic - Clear	None Detected
B-17A - Tile	Unit #10 Bathroom	12 x 12 Floor Tile - Various	None Detected
B-17A - Mastic	"	Mastic - Clear	None Detected
B-17B - Tile	"	12 x 12 Floor Tile - Various	None Detected
B-17B - Mastic	"	Mastic - Clear	None Detected
B-17C - Tile	"	12 x 12 Floor Tile - Various	None Detected
B-17C - Mastic	"	Mastic - Clear	None Detected
B-18A	Unit #10 Bathroom	Linoleum - Various	10% Chrysotile
B-18B	"	"	Stop Positive (Not Analyzed)
B-18C	"	"	Stop Positive (Not Analyzed)
B-19A	Unit #11 Hall & Bathroom	Linoleum - Brown/White	10% Chrysotile
B-19B	"	"	Stop Positive (Not Analyzed)
B-19C	"	"	Stop Positive (Not Analyzed)
B-20A	Through Out	Plaster Walls/Ceilings - Brown	None Detected
B-20B	"	Plaster Walls/Ceilings - Various	None Detected
B-20C	"	Plaster Walls/Ceilings - Brown/White	None Detected
B-20D	"	Plaster Walls/Ceilings - Various	None Detected
B-20E	"	Plaster Walls/Ceilings - Various	None Detected
B-20F	"	Plaster Walls/Ceilings - Brown	None Detected
B-20G	"	Plaster Walls/Ceilings - Various	None Detected
B-20H	"	Plaster Walls/Ceilings - Various	None Detected
B-20I	"	Plaster Walls/Ceilings - Various	None Detected

SAMPLE NUMBER	LOCATION AREA	SAMPLE DESCRIPTION / COLOR	% ASBESTOS
B-21A	Through Out	Sheetrock Walls/Ceilings - Brown	None Detected
B-21B	"	Sheetrock Walls/Ceilings - Brown	None Detected
B-21C	"	Sheetrock Walls/Ceilings - Brown	None Detected
B-21D	"	Sheetrock Walls/Ceilings - White	None Detected
B-21E	"	Sheetrock Walls/Ceilings - White	None Detected
B-21F	"	Sheetrock Walls/Ceilings - Brown/White	None Detected
B-21G	"	Sheetrock Walls/Ceilings - Brown/White	None Detected
B-21H	"	Sheetrock Walls/Ceilings - White	None Detected
B-21I	"	Sheetrock Walls/Ceilings - Tan	None Detected
B-22A	Through Out	Joint Compound - Tan/White	None Detected
B-22B	"	"	None Detected
B-22C	"	"	None Detected
B-22D	"	"	None Detected
B-22E	"	"	None Detected
B-22F	"	"	None Detected
B-22G	"	"	None Detected
B-22H	"	"	None Detected
B-22I	"	"	None Detected
B-23A	Through Out 2nd Floor	Skim Coat Walls/Ceilings - Tan/White	None Detected
B-23B	"	"	None Detected
B-23C	"	"	None Detected
B-24A	Through Out 1st Floor	Skim Coat Walls/Ceilings - Various	None Detected
B-24B	"	"	None Detected
B-24C	"	"	None Detected
B-25A	Roof	Rolled Roofing - Various	None Detected
B-25B	"	"	None Detected
B-25C	"	"	None Detected
B-25D	"	"	None Detected
B-25E	"	"	None Detected
B-25F	"	"	None Detected
B-25G	"	"	None Detected
B-25H	"	"	None Detected
B-25I	"	"	None Detected

SAMPLE NUMBER	LOCATION AREA	SAMPLE DESCRIPTION / COLOR	% ASBESTOS
B-26A	Roof	Felts under New Shingles - Black	None Detected
B-26B	"	"	None Detected
B-26C	"	"	None Detected
B-26D	"	"	None Detected
B-26E	"	"	None Detected
B-26F	"	"	None Detected
B-26G	"	"	None Detected
B-26H	"	"	None Detected
B-26I	"	"	None Detected
B-27A	Attic	Insulation - Brown/White	None Detected
B-27B	"	"	<0.25% Chrysotile
B-27C	"	"	<0.25% Chrysotile



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08108

Phone: (353) 850-4000 Fax: (353) 850-4000 Email: westmonta@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267
EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 6 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B1A TILE, B1A MASTIC, B1B TILE, B1B MASTIC, B1C TILE, B1C MASTIC, B2A LINOLEUM, B2A MASTIC.

Analyst(s)

Dave Poitras (125)

Handwritten signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08108

Phone: (856) 833-4300 Fax: (856) 833-4366 Email: westmont@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267
EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B2B LINOLEUM, B2B MASTIC, B2C LINOLEUM, B2C MASTIC, B3A, B3B, B3C, and B4A.

Analyst(s)
Dave Poitras (125)

Signature of Stephen Siegel
Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08108

Phone: (856) 958-4300 Fax: (856) 958-4300 Email: westmontlab@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B4B, B4C, B5A, B5B, B5C, B6A, B6B, B6C.

Analyst(s)

Dave Poitras (125)

Signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08105

Phone: (609) 856-4800 Fax: (609) 856-4900 Email: westmontaslab@EMSL.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267
EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B7A, B7B, B7C, B8A TILE, B8A MASTIC, B8B TILE, B8B MASTIC, B8C TILE.

Analyst(s)

Dave Poitras (125)

Signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08100

Phone: (202) 853-4600 Fax: (856) 853-1000 Email: westmont@hick2.EMSL.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax:
Phone: (207) 854-2711
Project: 130 EASTERN PROM/07-178

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B8C MASTIC, B9A TILE, B9A MASTIC, B9B TILE, B9B MASTIC, B9C TILE, B9C MASTIC, and B10A.

Analyst(s)

Dave Poitras (125)

Handwritten signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08107

Phone: (853) 858-4800 Fax: (853) 858-4960 Email: westmont@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with columns: Sample, Location, Appearance, Non-Asbestos (% Fibrous, % Non-Fibrous), Asbestos (% Type). Rows include B10B, B10C, B11A, B11B, B11C, B12A LINOLEUM, B12A MASTIC, B12B LINOLEUM.

Analyst(s)

Dave Poitras (125)

Handwritten signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08102

Phone: (856) 856-1000 Fax: (856) 856-4580 Email: westmontlab@EMSL.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B12B MASTIC, B12C LINOLEUM, B12C MASTIC, B13A TILE, B13A MASTIC, B13B TILE, B13B MASTIC, B13C TILE.

Analyst(s)

Dave Poitras (125)

Signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



Attn: **Mark Griffeth**
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
 Customer PO:
 Received: 08/09/07 9:40 AM
 EMSL Order: 040719267

Fax:
 Project: 130 EASTERN PROM/07-178

Phone: (207) 854-2711
 EMSL Proj:
 Analysis Date: 8/13/2007
 Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Location	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
B13C MASTIC 040719267-0039A	LIVING ROOM	Clear Non-Fibrous Homogeneous		100% Non-fibrous (other)	None Detected
B14A 040719267-0040	LIVING ROOM & BEDROOM	Brown/White Fibrous Heterogeneous	60% Cellulose 10% Min. Wool	30% Non-fibrous (other)	None Detected
B14B 040719267-0041	LIVING ROOM & BEDROOM	Brown/White Fibrous Heterogeneous	60% Cellulose 10% Min. Wool	30% Non-fibrous (other)	None Detected
B14C 040719267-0042	LIVING ROOM & BEDROOM	Brown/White Fibrous Heterogeneous	60% Cellulose 10% Min. Wool	30% Non-fibrous (other)	None Detected
B15A 040719267-0043	CLOSET	Various Fibrous Heterogeneous	78% Cellulose 2% Hair	20% Non-fibrous (other)	None Detected
B15B 040719267-0044	CLOSET	Various Fibrous Heterogeneous	78% Cellulose 2% Hair	20% Non-fibrous (other)	None Detected
B15C 040719267-0045	CLOSET	Various Fibrous Heterogeneous	78% Cellulose 2% Hair	20% Non-fibrous (other)	None Detected
B16A TILE 040719267-0046	BATHROOM	Gray/White Non-Fibrous Heterogeneous		100% Non-fibrous (other)	None Detected

Analyst(s)

Dave Poitras (125)

Stephen Siegel, CIH, Laboratory Manager
 or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08108

Phone: (856) 656-1600 Fax: (856) 656-1600 Email: westmontash@EMSL.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax: Phone: (207) 854-2711
Project: 130 EASTERN PROM/07-178

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 6 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B16A MASTIC, B16B TILE, B16B MASTIC, B16C TILE, B16C MASTIC, B17A TILE, B17A MASTIC, B17B TILE.

Analyst(s)

Dave Poitras (125)

Signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08108

Phone: (856) 850-4000 Fax: (856) 850-4000 Email: westmont@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax: Phone: (207) 854-2711
Project: 130 EASTERN PROM/07-178

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 6 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B17B MASTIC, B17C TILE, B17C MASTIC, B18A, B18B, B18C, B19A, B19B.

Analyst(s)

Dave Poitras (125)

Signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08108

Phone: (856) 859-4800 Fax: (856) 858-4960 Email: westmontashlab@EMSL.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax: Phone: (207) 854-2711
Project: 130 EASTERN PROM/07-178

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include B19C, B20A, B20B, B20C, B20D, B20E, B20F, B20G.

Analyst(s)

Dave Poitras (125)

Handwritten signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08106

Phone: (202) 258-4800 Fax: (856) 958-4360 Email: westmont@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax:
Project: 130 EASTERN PROM/07-178
Phone: (207) 854-2711

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Table with 7 columns: Sample, Location, Appearance, % Fibrous, % Non-Fibrous, Asbestos % Type. Rows include samples B26B, B26C, B26D, B26E, and B27A with their respective analysis results.

CERT# BA-0093

Analyst(s)

Dave Poitras (125)

Signature of Stephen Siegel

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Due to magnification limitations inherent in PLM, asbestos fibers in dimensions below the resolution capability of PLM may not be detected. Samples reported as <1% or none detected may require additional testing by TEM to confirm asbestos quantities. The limit of detection as stated in the method is 1%. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL Analytical, Inc. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Analysis performed by EMSL Westmont (NVLAP #101048-0), NY ELAP 10872



EMSL Analytical, Inc.

107 Haddon Ave., Westmont, NJ 08109

Phone: (856) 856-4600 Fax: (856) 858-4600 Email: westmontlab@emsl.com

Attn: Mark Griffeth
Environmental Safety & Hygiene Assoc.
5 Delta Drive
Westbrook, ME 04092

Customer ID: ESH50
Customer PO:
Received: 08/09/07 9:40 AM
EMSL Order: 040719267

Fax: Phone: (207) 854-2711
Project: 130 EASTERN PROM/07-178

EMSL Proj:
Analysis Date: 8/13/2007
Report Date: 8/13/2007

Asbestos Analysis of Bulk Material via EPA 600/R-93/116. Quantitation using 400 Point Count Procedure.

Sample	Location	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
B27B 040719267-0102	ATTIC	Brown/White Fibrous Homogeneous	98.00% Cellulose 2.00% Min. Wool		<0.25% Chrysotile
B27C 040719267-0103	ATTIC	Brown/White Fibrous Homogeneous	98.00% Cellulose 2.00% Min. Wool		<0.25% Chrysotile

CERT# BA-0093

Analyst(s)

Dave Poitras (2)

Stephen Siegel, CIH, Laboratory Manager
or other approved signatory

Disclaimer: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval of EMSL Analytical Inc. This test report must not be used by the client to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc., bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layered samples. EMSL Analytical Inc., liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Analysis performed by EMSL Test Lab (NVLAP #101048-0), NY ELAP 10872

Casco Bay Ventures ·
130 Eastern Prop. Pkld ·
Chain of Custody



Asbestos Lab Services

EMSL Analytical, Inc.
107 Haddon Avenue
Westmont, NJ 08108

Phone: (856) 858-4800
Fax: (856) 858-4960
(856) 427-1608
<http://www.emsl.com>

Please print all information legibly.

040719267-

Company:	ESHA	Bill To:	ESHA
Address 1:	5 Delta Drive	Address 1:	5 Delta Drive
Address 2:		Address 2:	
City, State:	Westbrook, Maine	City, State:	Westbrook, Maine
Zip/Post Code:	04092	Zip/Post Code:	04092
Country:	USA	Country:	USA
Contact Name:	MARK GRIFLETTH	Attn:	Mark Coleman
Phone:	207-854-2711	Phone:	207-854-2711
Fax:	207-854-2609	Fax:	207-854-2609
Email:	MR6@ESHA.NET	Email:	MPC@ESHA.NET
EMSL Rep:		P.O. Number:	
Project Name/Number: 130 EASTERN PROP / 07-178			

MATRIX			TURNAROUND			
<input type="checkbox"/> Air	<input type="checkbox"/> Soil	<input type="checkbox"/> Micro-Vac	<input type="checkbox"/> 3 Hours	<input type="checkbox"/> 6 Hours	<input type="checkbox"/> Same Day or 12 Hours*	<input type="checkbox"/> 24 Hours (1 day)
<input checked="" type="checkbox"/> Bulk	<input type="checkbox"/> Drinking Water		<input type="checkbox"/> 48 Hours (2 days)	<input checked="" type="checkbox"/> 72 Hours (3 days)	<input type="checkbox"/> 96 Hours (4 days)	<input type="checkbox"/> 120 Hours (5 days)
<input type="checkbox"/> Wipe	<input type="checkbox"/> Wastewater		<input type="checkbox"/> 144+ hours (6-10 days)			

TEM AIR, 3 hours, 6 hours, Please call ahead to schedule. There is a premium charge for 3-hour tat, please call 1-800-220-3675 for price prior to sending samples. You will be asked to sign an authorization form for this service.

*12 hours (must arrive by 11:00a.m. Mon -Fri), Please Refer to Price Quote

PCM - Air <input type="checkbox"/> NIOSH 7400(A) Issue 2, August 1994 <input type="checkbox"/> OSHA w/TWA <input type="checkbox"/> Other:	TEM Air <input type="checkbox"/> AHERA 40 CFR, Part 763 Subpart E <input type="checkbox"/> NIOSH 7402 <input type="checkbox"/> EPA Level II	TEM WATER <input type="checkbox"/> EPA 100.1 <input type="checkbox"/> EPA 100.2 <input type="checkbox"/> NYS 198.2
PLM - Bulk <input checked="" type="checkbox"/> EPA 600/R-93/116 <input type="checkbox"/> EPA Point Count <input type="checkbox"/> NY Stratified Point Count <input type="checkbox"/> PLM NOB (Gravimetric) NYS 198.1 <input type="checkbox"/> NIOSH 9002: <input type="checkbox"/> EMSL Standard Addition:	TEM BULK <input type="checkbox"/> Drop Mount (Qualitative) <input type="checkbox"/> Chatfield SOP - 1988-02 <input type="checkbox"/> TEM NOB (Gravimetric) NYS 198.4 <input type="checkbox"/> EMSL Standard Addition:	TEM Microvac/Wipe <input type="checkbox"/> ASTM D 5755-95 (quantitative method) <input type="checkbox"/> Wipe Qualitative
SEM Air or Bulk <input type="checkbox"/> Qualitative <input type="checkbox"/> Quantitative	PLM Soil <input type="checkbox"/> EPA Protocol Qualitative <input type="checkbox"/> EPA Protocol Quantitative <input type="checkbox"/> EMSL MSD 9000 Method fibers/gram	XRD <input type="checkbox"/> Asbestos <input type="checkbox"/> Silica NIOSH 7500 OTHER <input type="checkbox"/>

SAMPLES ACCEPTED FOR ANALYSIS BY
 EMSL ANALYTICAL, INC.
 WESTMONT, NJ 08108
 TEL: (856) 858-4800
 FAX: (856) 858-4960

040719267-

Chain of Custody

page #1 07-178
Asbestos Lab Services

EMSL Analytical, Inc.
107 Haddon Avenue
Westmont, NJ 08108

Phone: (856) 858-4800
Fax: (856) 858-4960
(856) 427-1608
http://www.emsl.com

Please print all information legibly.

Client Sample # (s) B-1 - B27C

Total Samples #: 103

Relinquished: [Signature] Date: 8-8-07

Time: 3:40pm

Received: DOM - FX-940A Date: _____

Time: _____

Relinquished: _____ Date: _____

Time: _____

Received: _____ Date: _____

Time: _____

	SAMPLE NUMBER	SAMPLE DESCRIPTION/LOCATION	VOLUME (if applicable)
UNIT #3	B1A-C	12"x12" Floor Tile Kitchen	75 FT ²
	B2A-C	Linoleum Kitchen	75 FT ² +
	B3A-C	Linoleum closet Tan	4 FT ²
	B4A-C	Linoleum closet Brown	4 FT ²
	B5A-C	1'x1' ceiling Tile - pine Hole ^{Living}	120 FT ²
	B6A-C	1'x1' ceiling Tile - Textured ^{Dining}	120 FT ²
SAME AS UNIT #7 KITCHEN & B2	B7A-C	1'x1' ceiling Tile Smooth ^{Bedroom}	240 FT ²
	B8A-C	9"x9" Floor Tile Bathroom	6 FT ² +
UNIT #4	B9A-C	12"x12" over 9"x9" Floor Tile Gray Bathroom	35 FT ²
UNIT #6	B10A-C	9"x9" Floor Tile Green Bathroom	30 FT ²
	B11A-C	Linoleum Pantry	6 FT ²

SAMPLES ACCEPTED FOR ANALYSIS BY EMSL ANALYTICAL INC.

