EMSL Analytical, Inc.
161 John Roberts Road South Portland, ME 04106
Tel/Fax: (207) 517-6921 / (207) 517-6922
http://www.EMSL.com / portlandlab@emsl.com

EMSL Order: 621601499
Customer ID: ABAT52
Customer PO: 140
Project ID:

Reviewed for Code Compliance
Inspections Division
Approved with Conditions
Date: 10/31/16

Attention: Bob Rickett
Abatement Professionals Corporation
590 County Road
Suite #2
Westbrook, ME 04092
Project: FORE ST, PORTLAND

Phone: (207) 671-4361
Fax: (207) 772-1203
Received Date: 09/28/2016 11:52 AM
Analysis Date: 09/29/2016
Collected Date:

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

			Non-Asbestos		Asbestos
Sample	**Description**	**Appearance**	**% Fibrous**	**% Non-Fibrous**	**% Type**
B-1-A *621601499-0001*	SIDING MATERIAL	Black Fibrous Homogeneous	8% Cellulose	92% Non-fibrous (Other)	None Detected
B-1-B *621601499-0002*	SIDING MATERIAL	Black Fibrous Homogeneous	6% Cellulose	94% Non-fibrous (Other)	None Detected
B-1-C *621601499-0003*	SIDING MATERIAL	Black Fibrous Homogeneous	6% Cellulose	94% Non-fibrous (Other)	None Detected

Report Comment: **Maine Certification # BA-0174**

Analyst(s)
Zackary Carbee (3)

CWalker
Christina Walker, Laboratory Manager
or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Samples received in good condition unless otherwise noted. Estimated accuracy, precision and uncertainty data available upon request. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Reporting limit is 1%

Samples analyzed by EMSL Analytical, Inc. South Portland, ME NVLAP Lab Code 500094-0, Massachusetts AA000236, Vermont AL197271

Initial report from: 09/29/2016 11:50:11