

ARCHITECTURE
SECTION 02466
DRILLED PILES

PART 1 - GENERAL

1.1 SUMMARY

- A. Section includes dry-installed drilled piles.

1.2 UNIT PRICES

- A. Unit prices are included in Division 1 Section "Unit Prices."
- B. Drilled Piles: Actual net volume of drilled piles in place and approved. Actual length, shaft diameter, may vary, to coincide with elevations where satisfactory bearing strata are encountered. These dimensions may also vary with actual bearing value of bearing strata determined by an independent testing and inspecting agency. Adjustments will be made on net variation of total quantities, based on design dimensions for shafts.
 - 1. Base bids on indicated number of drilled piles and, for each pile, the design length from top elevation to bottom of shaft as recommended by Geotechnical Engineering summary report, and the diameter of shaft.
 - 2. Unit prices include labor, materials, tools, equipment, and incidentals required for excavation, trimming, shoring, casings, dewatering, reinforcement, concrete fill, testing and inspecting, and other items for complete drilled-pile installation.

1.3 SUBMITTALS

- A. Product Data: For each type of product indicated.
- B. Design Mixtures: For each concrete mixture.
- C. Shop Drawings: For concrete reinforcement, if required.
- D. Welding certificates.
- E. Material certificates.

1.4 QUALITY ASSURANCE

- A. Welding Qualifications: Qualify procedures and personnel according to the following:
 - 1. AWS D1.1/D1.1M, "Structural Welding Code - Steel."
- B. Preinstallation Conference: Conduct conference at Project site.

1.5 PROJECT CONDITIONS

- A. Project-Site Information: A geotechnical report has been prepared for this Project and is available for information only. The opinions expressed in this report are those of geotechnical engineer and represent interpretations of subsoil conditions, tests, and results of analyses conducted by geotechnical engineer. Owner will not be responsible for interpretations or conclusions drawn from this data.
 - 1. Make additional test borings and conduct other exploratory operations necessary for drilled piles.
 - 2. The geotechnical report is included elsewhere in the Project Manual.
- B. Survey Work: Engage a qualified land surveyor or professional engineer to perform surveys, layouts, and measurements for drilled piles. Before excavating, lay out each drilled pile to lines

ARCHITECTURE

and levels required. Record actual measurements of each drilled pile's location, shaft diameter, bottom and top elevations, deviations from specified tolerances, and other specified data.

1. Record and maintain information pertinent to each drilled pile and cooperate with Owner's testing and inspecting agency to provide data for required reports.

PART 2 - PRODUCTS

2.1 STEEL REINFORCEMENT, if required.

- A. Reinforcing Bars: ASTM A 615/A 615M, **Grade 60 (Grade 420)**, deformed.
- B. Plain-Steel Wire: ASTM A 82, galvanized.

2.2 CONCRETE MATERIALS

- A. Cementitious Material: Use the following cementitious materials, of same type, brand, and source, throughout Project:
 1. Portland Cement: ASTM C 150.
- B. Normal-Weight Aggregate: ASTM C 33, graded, **3/4-inch- (19-mm-)** nominal maximum coarse-aggregate size.
- C. Water: ASTM C 94/C 94M and potable.
- D. Chemical Admixtures: Provide admixtures certified by manufacturer to be compatible with other admixtures and that will not contribute water-soluble chloride ions exceeding those permitted in hardened concrete. Do not use calcium chloride or admixtures containing calcium chloride.
 1. Water-Reducing Admixture: ASTM C 494/C 494M, Type A.
 2. Water-Reducing and Retarding Admixture: ASTM C 494/C 494M, Type D.

2.3 STEEL PIPE

- A. Steel Pipe: ASTM A 283/A 283M, Grade C, or ASTM A 36/A 36M, carbon-steel plate, with joints full-penetration welded according to AWS D1.1/D1.1M.

2.4 CONCRETE MIXTURES AND MIXING

- A. Prepare design mixtures for each type and strength of concrete, proportioned on the basis of laboratory trial mixture or field test data, or both, according to ACI 301.
- B. Cementitious Materials: Limit percentage, by weight, of cementitious materials other than portland cement according to ACI 301 limits as if concrete were exposed to deicing chemicals.
- C. Limit water-soluble, chloride-ion content in hardened concrete to 0.15 percent by weight of cement.
- D. Proportion normal-weight concrete mixture as follows:
 1. Compressive Strength (28 Days): **4000 psi (27.6 MPa)**.
 2. Air Content: Do not air entrain concrete.
- E. Ready-Mixed Concrete: Measure, batch, mix, and deliver concrete according to ASTM C 94/C 94M, and furnish batch ticket information.

ARCHITECTURE

PART 3 - EXECUTION

3.1 EXCAVATION

- A. **Unclassified Excavation:** Excavate to bearing elevations regardless of character of surface and subsurface conditions encountered.
- B. **Notify and allow testing and inspecting agency to test and inspect bottom of excavation.** If unsuitable bearing stratum is encountered, make adjustments to drilled piles as determined by Architect.
 - 1. Do not excavate shafts deeper than elevations indicated unless approved by Architect.
 - 2. Payment for additional authorized excavation will be according to Contract provisions for changes in the Work.
- C. **End-Bearing Drilled Piles:** Probe with auger to a depth below bearing elevation, equal to diameter of the bearing area of drilled pile. Determine whether voids, clay seams, or solution channels exist.
- D. **Tolerances:** Construct drilled piles to remain within ACI 336.1 tolerances.

3.2 INSTALLATION

- A. Install steel pipe of minimum wall thickness indicated for the required capacity listed on the drawings.
- B. Comply with recommendations in CRSI's "Manual of Standard Practice" for fabricating, placing, and supporting reinforcement.
- C. Place concrete in continuous operation and without segregation immediately after inspection and approval of shaft by Owner's independent testing and inspecting agency.

3.3 FIELD QUALITY CONTROL

- A. **Special Inspections:** Owner will engage a qualified special inspector to perform the following special inspections:
 - 1. Drilled piles.
 - 2. Concrete.
 - 3. Steel reinforcement welding.
- B. **Concrete Tests and Inspections:** ACI 301.

END OF SECTION 02466