



**PROJECT MANUAL AND SPECIFICATIONS
FOR
FORE STREET PARKING FACILITY
PHASE VII RESTORATION
and
STAIR #1 CURTAIN WALL**



Prepared by:

Becker Structural Engineers, Inc.
BSE Project No. W0 3144
Engineer: Todd M. Neal, P.E.

Issued for Permit:
OCTOBER 11, 2013

TABLE OF CONTENTS

Division 1 – General Requirements

01300	Submittals
01500	Construction Facilities and Temporary Controls
01710	Cleaning

Division 2 – Existing Conditions

02070	Selective Demolition
-------	----------------------

Division 3 – Concrete

03310	Concrete Repair
-------	-----------------

Division 5 – Metals

05120	Structural Steel
-------	------------------

Division 7 – Thermal and Moisture Protection

07180	Traffic Coatings
07920	Joint Sealant

Division 9 – Finishes

09900	Painting
-------	----------

Drawings

S1.1	Grade Level Slab Plan
S1.2	1 st Supported Level Slab Plan
S1.3	2 nd Supported Level Slab Plan
S1.3	3 rd Supported Level Slab Plan
S1.4	Stair #1 Curtain Wall Demo/New Work Plan
S3.1	Typical Concrete Repair Sections and Details
S3.2	General Notes and Membrane Details
S3.3	Curtain Wall Elevation/Section

DIVISION 1

GENERAL REQUIREMENTS

SECTION 01300

SUBMITTALS

PART 1 GENERAL

1.01 GENERAL REQUIREMENTS

- A. The CONDITIONS OF THE CONTRACT, all Drawings, and all Sections of Division 1 are hereby made a part of this Section.

1.02 WORK INCLUDED

- A. This Section specifies administrative and procedural requirements for submittals required for performance of work, including:

1. Product data
2. Shop drawings

- B. Administrative Submittals: Refer to requirements specified in other Division 1 Specification Sections, and other Contract Documents, for administrative submittals, including:

1. Permits
2. Applications for payment
3. Performance and payment bonds (where required).
4. Insurance certificates
5. List of subcontractors

1.03 RELATED REQUIREMENTS

- A. Examine Contract Documents for requirements that affect Work of this Section. Other Specification Sections that directly relate to Work of this Section include, but are not limited to:

1. Concrete Repair: SECTION 03310
2. Structural Steel: SECTION 05120
3. Traffic Coating: SECTION 07180
4. Joint Sealants: SECTION 07920

1.04 SUBMITTAL PROCEDURES

- A. Coordination of Submittals: Coordinate timing of submittals with construction activities. Transmit submittals well enough in advance of performance of work to avoid delays. Coordinate submittals of related elements of work.
 - 1. Engineer may reject, or withhold action on submittals requiring coordination with other submittals until related submittals are received.
- B. Processing of Submittals: Allow sufficient review time to ensure installation will not be delayed because of time required to process submittals. Minimum processing times are as follows:
 - 1. Review by Engineer: Allow ten (10) business days for review and processing.
 - 2. No extension of Contract Time will be authorized due to failure to transmit submittals sufficiently in advance of scheduled performance of work.
- C. Contractors Preparation of Submittals: Place permanent label or title block on each submittal for identification. Indicate Project Name, Engineer's Project Number, Specification Section number and title, date of submittal, name and address of Engineer, name and address of Contractor, name and address of subcontractor and/or supplier, name of manufacturer, Drawing number and detail reference.
 - 1. Contractor's Review and Action Stamp: Provide suitable space on label or title block for Contractor's review and action stamp. Stamp and sign each submittal to show Contractor's review and approval prior to transmittal to Engineer. Submittals not signed and stamped by Contractor will be returned without action.
 - 2. Engineer's Review and Action Stamp: Provide minimum 6 in. x 4 in. space on drawing for Engineer's review and action stamp. Deliver submittals to Engineer at address listed on cover of Project Manual.
 - 3. Modify and customize submittals as required to show interface with adjacent work and attachment to building.
- D. Transmittal of Submittals: Transmit each item with transmittal form. Identify Project, Contractor, subcontractor, major supplier; identify pertinent Drawing sheet and detail number and Specification section number, as appropriate, on transmittal form.
 - 1. Source: Submittals received from sources other than Contractor will be returned without action.

2. Deviations from Contract Documents: When products, materials or systems submitted deviate from Contract Documents, record deviations clearly on transmittal form, or separate attached sheet.
 3. If deviation includes design and/or material change, this shall be accompanied by design calculations stamped by a registered professional Engineer or additional time and fee (payable by Contractor) will be required for submittal review.
- E. Before submitting each Shop Drawing or Sample, Contractor shall have determined and verified:
1. All field measurements, quantities, dimensions, specified performance and design criteria, installation requirements, materials, catalog numbers, and similar information with the respect thereto;
 - a. the suitability of all materials with respect to the intended use, fabrication, shipping, handling, storage, assembly, and installation pertaining to the performance of the Work;
 - b. all information relative to the Contractor's responsibilities for means, methods, techniques, sequences, and procedures of construction, and safety precautions and programs incident thereto; and
 - c. shall also have reviewed and coordinated each Shop Drawing or Sample with other Shop Drawings and Samples and with the requirements of the Work and the Contract Documents.
- F. Each Submittal shall bear a stamp or specific written certification that Contractor has satisfied Contractor's obligations under the Contract Documents with respect to Contractor's review and approval of that submittal.
- G. With each Submittal, Contractor shall give Engineer specific written notice of any variations, that the Shop Drawing or Sample may have from the requirements of the Contract Documents. This notice shall be both a written communication separate from the Shop Drawing's or Sample Submittal; and, in addition, by a specific notation made on each Shop Drawing or Sample submitted to Engineer for review and approval of each such variation.
- H. After Engineer reviews submittal, revise and resubmit as required. Identify recipients to promptly report inability to comply with provisions.
- I. Distribute copies of reviewed submittals to concerned persons. Instruct recipients to promptly report inability to comply with provisions.

1.05 SUBMITAL SCHEDULE

- A. Not required for this project.

1.06 SHOP DRAWINGS

- A. Provide accurately prepared, large scale and detailed shop drawings prepared specifically for this Project on reproducible sheets. Show adjacent conditions and related work. Show accurate field dimensions where appropriate. Identify materials and products shown. Note special coordination required. Standard information prepared without specific reference to Project is not considered shop drawings.
- B. Shop drawings include fabrication and installation drawings, setting diagrams, schedules, patterns, templates, and similar drawings.
- C. Show every component of fabricated item, notes regarding manufacturing process, coatings and finishes, identifying numbers conforming to Contract Documents, (i.e. stair numbers, door numbers, etc.) dimensions, and appropriate trade names. Show anchorage and fastening details, include type, size and spacing. Show material gage and thickness. Indicate welding details and joint types.
- D. Show Drawing Sheet Size: Except for templates, patterns, and other full-size drawings, submit shop drawings on sheets at least 8-1/2 in. x 11 in., but no larger than 24 in. x 36 in.
- E. Submittal Quantities: Submit shop drawings in following quantities:
 - 1. For shop drawings submitted for Engineer's review, submit **one** reproducible and **two** black line prints of each sheet. Reproducible will be returned to Contractor for printing and distribution. **Multiple copies will not be marked by Engineer.**

1.07 PRODUCT DATA

- A. Definition: Product data includes manufacturer's standard published literature, such as installation instructions, catalog cuts and color charts. When product data must be prepared specifically because standard published data is not suitable for use, submit as shop drawing.
- B. Preparation: Mark each copy of product data to show applicable choices and options. Where published product data includes information on several products and choices, mark copies to clearly indicate information applicable to this Project.
- C. Do not submit product data until compliance with requirements of Contract Documents has been confirmed.

- D. Submittal Quantities: Submit product data in following quantities:
1. Submit three copies for review. One copy will be returned to Contractor for printing and distribution. Multiple copies will not be marked by Engineer.
- E. Installer Copy: Verify that installer of work possesses a current copy of Engineer approved product data prior to installation.
- 1.08 ENGINEER'S ACTION
- A. Engineer's review and approval will not extend to means, methods, techniques, sequences, or procedures (except where a particular means, method, technique, sequence, or procedure of construction is specifically and expressly called for by the Contract Documents) or to safety precautions or programs incident thereto. The review and approval of a separate item as such will not indicate approval of the assembly in which the item functions.
- B. Engineer's review and approval shall not relieve the Contractor from responsibility for any variation from the requirements of the Contract Documents unless Contractor has complied with all requirements of this section, the general and supplementary conditions of the Contract and the Engineer has given approval of each such variation by specific written notation thereof incorporated in or accompanying the Shop Drawing or Sample. Engineer's review and approval shall not relieve Contractor from responsibility for complying with the requirements of paragraph 1.04.
- 1.09 DISTRIBUTION BY CONTRACTOR
- A. Distribution: When submittal is marked "APPROVED" or "APPROVED AS NOTED", make prints and copies and distribute to subcontractors, suppliers, fabricators, and other parties requiring information from submittal for proper coordination and performance of work. Print copies of shop drawings from approved reproducible only.

END OF SECTION

SECTION 01500

CONSTRUCTION FACILITIES AND TEMPORARY CONTROLS

PART 1 GENERAL

1.01 GENERAL REQUIREMENTS

- A. Drawings, Contract Conditions, and other Technical Specifications Sections apply to work of this Section insofar as applicable.

1.02 WORK INCLUDED

- A. This Section specifies construction facilities and temporary controls, including, but not limiting to:
 - 1. Temporary restrictions on construction activity.
 - 2. Temporary utilities.
 - 3. Temporary construction and support facilities.
 - 4. Temporary signage.
 - 5. Security and protection facilities.
- B. Contractor shall pay for all costs related to temporary facilities and utility service including but not limited to temporary heat, water and power. If required.

1.03 RELATED REQUIREMENTS

- A. Examine Contract Documents for requirements that affect work of this Section. Other Specification Sections that directly relate to work of this Section include, but are not limited to:
 - 1. SECTION 00520: Contract Agreement
 - 2. SECTION 00700: General Conditions
 - 3. SECTION 01300: SUBMITTALS

1.04 QUALITY ASSURANCE

- A. Comply with requirements of authorities having jurisdiction, codes, utility companies, OSHA, and industry standards including, but not limiting to:
 - 1. NFPA 241.

2. NFPA 70.
 3. ANSI A10.
 4. NECA NJG-6.
- B. Electric Service: Comply with NEMA, NECA, and UL standards and regulations for temporary electric service. Install service in compliance with NFPA 70.
- C. Inspections: Arrange for authorities having jurisdiction to inspect temporary utilities prior to use. Obtain required certifications and permits.

1.05 PROJECT CONDITIONS

- A. Conditions of Use: Maintain temporary services and facilities clean and neat in appearance. Operate in a safe and efficient manner. Take necessary fire prevention measures. Do not overload temporary facilities. Do not allow hazardous, dangerous, or unsanitary conditions to develop on site.

PART 2 PRODUCTS

2.01 MATERIALS, GENERAL

- A. Materials may be new or used, but must be adequate in capacity for the required usage, must not create unsafe conditions, and must not violate requirements of applicable codes and standards.
- B. Lumber and Plywood:
1. Signs and Directory Boards: Provide exterior grade, Medium Density Overlay (MDO) plywood, conforming to USDC PS1, of size and thickness indicated.
 2. Fences, Vision Barriers, and Safety Barriers: Provide exterior grade, C-D veneered plywood.

2.02 TEMPORARY UTILITIES

- A. Scope: Temporary utility work includes, but is not limited to:
1. Electric power
 2. Telephone Service.
- B. Temporary Electric Power and Light:
1. Power is currently available in the garage and can be used. Not all outlets are currently operational and may not provide easy access to all areas of work. Additional power maybe required and should be provided by the contractor.

2. Provide generator to run any equipment that exceeds the capacity of the existing system.

C. Telephone Service: Provide cell phone contact for project superintendent and project manager for this project.

2.03 TEMPORARY CONSTRUCTION AND SUPPORT FACILITIES

A. Scope: Temporary construction and support facilities include, without limitation:

1. Temporary heat.
2. Temporary enclosures.
3. Construction aids.
4. Waste disposal services.
5. Water control.
6. Rodent and pest control.
7. Pollution and dust control.

B. Temporary Heat and Ventilation: Provide temporary heat and ventilation required to maintain adequate environmental conditions to facilitate progress of work, to meet manufacturers' specified minimum installation conditions, and to protect materials and finishes from damage due to temperature and humidity.

1. Ventilate enclosed areas for curing of installed materials, to disperse humidity, and to prevent hazardous accumulations of dust, fumes, vapors and gases.
2. Portable heaters shall be standard approved units with controls.
3. Pay costs of installation, maintenance, operation, removal, and fuel consumed.

C. Contractor's Field Offices and Sheds: Prior to installation of offices and sheds, consult with Engineer and Owner on location, access, and related facilities.

D. Sanitary Facilities: Toilet facilities within the building will be available.

1. Maintain washrooms in clean and sanitary condition and supply exhaustible materials such as soap, hand towels, and toilet tissue.

E. Temporary Enclosures: Provide temporary weathertight enclosures of exterior walls as Work progresses. Design and construct temporary enclosures to provide acceptable working conditions, to provide weather protection for materials, to allow effective temporary heating, and to prevent entry of unauthorized persons.

1. Provide temporary exterior doors with self-closing hardware and padlocks.
 2. Design enclosures to be removable to allow handling of materials.
- F. Construction Aids: Provide construction aids and equipment required by personnel to facilitate execution of the work; scaffolds, staging, ladders, stairs, ramps, runways, platforms, railings, hoists, cranes, chutes, and other such facilities and equipment.
1. Refer to respective sections for particular requirements for each trade.
- G. Use of Elevator: Will not be permitted for construction use.
- H. Waste Disposal: Maintain all areas under Contractor's control free of debris. Initiate and maintain a specific program to prevent accumulation of debris at construction area, storage and parking areas.
1. Provide containers for deposit of debris.
 2. Schedule daily collection and weekly disposal of debris.
 3. Provide additional collections and disposals of debris whenever the weekly schedule is inadequate to prevent accumulation.
- I. Water Control: Provide methods to control surface water to prevent damage to Project, site, and adjoining properties.
- J. Dispose of drainage water in a manner to prevent flooding, erosion, or other damage to any portion of the site or to adjoining areas and properties.
- K. Pollution Control: Provide methods, means, and facilities required to prevent contamination of soil, water, or atmosphere by the discharge of noxious substances from construction operations. Provide equipment and personnel, perform emergency measures required to contain any spillage and to remove contaminated soils or liquids.
1. Take special measures to prevent harmful substances from entering public waters.
 2. Prevent disposal of wastes, effluents, chemicals, or other such substances in sanitary or storm sewers.
 3. Provide systems for control of atmospheric pollutants.
 4. Prevent toxic concentrations of chemicals.
 5. Prevent harmful dispersal of pollutants to atmosphere.

- L. Dust Control: Provide positive methods and apply dust control materials to minimize raising dust from construction/demolition operations. Provide positive means to prevent air-borne dust from dispersing into the atmosphere.

2.04 TEMPORARY SIGNAGE

- A. Scope: Temporary signage includes, but is not limited to:
 - 1. Traffic.
 - 2. Pedestrian.
 - 3. Means of Egress.
 - 4. Other signage as required in the Contract Documents.
- B. Sign Structure and Framing: New or used, wood or metal, in sound condition structurally adequate to work and suitable for specified finish.
- C. Rough Hardware: Galvanized steel or cadmium plated.
- D. Paint: Exterior quality.

2.05 SECURITY AND PROTECTION FACILITIES

- A. Scope: Security and protection facilities includes, but is not limited to:
 - 1. Temporary fire protection.
 - 2. Barricades, warning signs, lights.
 - 3. Temporary traffic control.
 - 4. Temporary access routes.
 - 5. Security procedures.
- B. Temporary Fire Protection: Provide and maintain suitable fire protection equipment and services. Establish procedures for fire protection for welding and other potentially hazardous construction operations. Ascertain and comply with requirements of Project insurance carrier, City of Portland Fire Department and the State of Maine Fire Marshal. Permanent fire protection system may be activated to meet these requirements. Replace fusible ink heads and other expended or discharged components at time of Substantial Completion.
 - 1. Locate temporary portable fire extinguishers in convenient locations, not less than one extinguisher per floor.

2. Store combustible materials in containers in fire-safe locations.
 3. Maintain unobstructed access to fire extinguishers, fire hydrants, temporary fire protection facilities, stairways, and other access routes.
- C. Barricades, Warning Signs, and Lights: Provide and maintain barricades, warning signs, warning lights, railings, walkways, and the like. Paint signs and barricades with appropriate colors, graphics, and warnings to inform public and job-site personnel of hazards.
- D. Construction Parking Control: Control vehicular parking to preclude interference with public traffic or parking, access by emergency vehicles, Owner's operations, or construction operations. Monitor parking of construction personnel's private vehicles:
1. Maintain free vehicular access to parking spaces and through parking garage.
 2. Prohibit parking on or adjacent to access roads, or in non-designated areas.
 3. Contractor has been provided with 60 spaces to complete work and for storage and contractor parking.
- E. Safety Controls and Safety Signing:
1. Detour signs shall have breakaway post assemblies conforming to the applicable provisions of MDOT Specifications.

PART 3 EXECUTION

3.01 MAINTENANCE, TERMINATION, AND REMOVAL

- A. Supervision: Enforce strict discipline in use of temporary facilities. Limit waste and abuse.
- B. Maintenance: Maintain temporary facilities in operating conditions; repair damages immediately upon discovery. Maintain operation of temporary enclosures, heating, cooling, humidity control, ventilation, and similar facilities on a 24-hour per day basis.
- C. Termination and Removal: Unless otherwise requested by Engineer, remove each temporary facilities when no longer useful, or when replaced by permanent facility. Clean and renovate permanent facilities that have been used during construction period.

END OF SECTION

**SECTION 01710
CLEANING**

PART 1 GENERAL

1.01 DESCRIPTION

- A. Work included: Throughout the construction period, maintain the buildings and site in a standard of cleanliness as described in this Section.
- B. Provide waste storage containers.
- C. Related work: In addition to standards described in this Section, comply with requirements for cleaning as described in pertinent other Sections of these Specifications.

1.02 QUALITY ASSURANCE

- A. Conduct inspections to verify that requirements for cleanliness are being met.

PART 2 – PRODUCTS

2.01 CLEANING MATERIALS AND EQUIPMENT

- A. Provide required personnel, equipment, and materials needed to maintain the specified standard of cleanliness.

2.02 COMPATIBILITY

- A. Use only the cleaning materials and equipment which are compatible with the surface being cleaned, as recommended by the manufacturer of the material.

2.03 WASTE STORAGE CONTAINER

- A. The Contractor is responsible for providing a suitable waste storage container of sufficient size or numbers for the temporary storage of wastes generated by the work of this Section and other Sections of these Specifications.
- B. The Contractor is responsible for the proper and timely transfer of stored wastes to a proper off-site disposal.
- C. Demolition debris shall not be stored on site.

PART 3 – EXECUTION

3.01 PROGRESS CLEANING

A. General:

1. Retain stored items in an orderly arrangement, in designated areas allowing maximum access, not impeding traffic or drainage, and providing required protection of materials.
2. Do not allow accumulation of scrap, debris, waste material, and other items not required for construction of this work, except in proper waste container(s).
3. Provide adequate storage for all debris and trash awaiting removal from the job site, observing requirements for fire protection and protection of the ecology.
4. Waste containers shall be emptied, off site, a minimum of once per week.

B. Site:

1. Continuously inspect the site and pick up all scrap, debris, and waste material. Remove such items to the container(s) designated for their storage.
2. Daily and more often if necessary, inspect all arrangements of construction materials stored on the site. Restack, organize neatly, tidy or otherwise service arrangements to meet requirements of subparagraph 3.01-A-1 above.

C. Building:

1. Daily, and more often if necessary, inspect and pick up all scrap, debris, and waste material. Remove such items to the container(s) designated for their storage.
2. As required preparatory to installation of succeeding materials, clean the surfaces to the degree of cleanliness recommended by the manufacturer of the succeeding material, using equipment and materials required to achieve the necessary cleanliness.

3.02 FINAL CLEANING

A. Prior to completion of the work, remove from the job site all tools, surplus materials, equipment, scrap, debris, and waste. Conduct final progress cleaning as described in Article 3.01 above.

B. Site:

1. Broom clean paved areas and slab used by construction.

2. Rake grass and garden areas to remove construction debris.
3. Completely remove resultant debris.

C. Building:

1. Exterior:

- a. Visually inspect exterior building surfaces and remove all traces of soil, waste materials, smudges, and other foreign matter caused by the work.
- b. Remove all traces of splashed materials from adjacent surfaces.

2. Interior:

- a. Visually inspect interior of building and remove all traces of soil, waste material, smudges, and other foreign matter caused by the work.
- b. Remove all unused construction material.
- c. Remove all temporary protection and shoring.
- d. Wash down all parking decks where work has been completed and/or affected by the work.

END OF SECTION

DIVISION 2
EXISTING CONDITIONS

SECTION 02070

SELECTIVE DEMOLITION

PART 1 GENERAL

1.01 DESCRIPTION

A. Work included: Remove the existing joint sealant, damaged concrete, and any other material as directed.

1. Removal of materials and debris includes proper site storage and off-site disposal. Should contractor discover, upon removal of damaged concrete, damage or deterioration of the embedded structural steel connections or reinforcement, they shall, immediately and prior to performing any repairs to these surfaces, inform the Engineer of encountered conditions. The Engineer will promptly review these conditions. As appropriate, the Engineer will provide the contractor with recommendations for repair of these conditions as described on the plans and in the specifications. Conform to all Federal, State and local safety requirements.

1.02 SUBMITTALS

Request for Engineer's consent:

1. Should conditions of the work, or schedule, indicate a required change of materials or methods for cutting and patching, so notify the Engineer and secure his written permission and the required Change Order prior to proceeding.

PART 2 PRODUCTS

2.01 TOOLS AND EQUIPMENT

- A. Provide the adequate tools and equipment necessary to carry out the work of this Section.
- B. Do not use tools, products and/or equipment which could damage the portions of the building which are to remain.
- C. Any repairs that are caused to sound material by the use of improper equipment shall be the responsibility of the contractor.

PART 3 EXECUTION

3.01 SURFACE CONDITIONS

A. Inspections:

2. Inspect existing conditions, including elements subject to movement or damage during cutting and patching.
3. After uncovering the work, inspect conditions affecting installation of new work.
4. Visually examine all areas of the project to determine actual conditions

B. Discrepancies:

5. If uncovered conditions are not as indicated, immediately notify the Engineer and secure needed directions prior to proceeding.
6. Do not proceed until written directions are obtained from the Engineer.

3.02 PREPARATION PRIOR TO CUTTING

- A. Contractor shall sound all concrete surfaces and confirm extent of repair area within locations marked on plan. The Engineer should be immediately notified of any discrepancies in quantities.
- B. Provide required protection including, but not necessarily limited to, shoring, bracing and support to maintain structural integrity of the work and existing members.
- C. Contractor shall construct barriers and other methods of protecting people and property prior to demolition.
 1. Barriers and other methods shall be constructed in a manner that is acceptable to the Owner and the Building Inspector.
- D. Barriers and other methods shall be maintained throughout construction.
 1. As a minimum, all portions of deck areas where demolition or construction is taking place shall be completely closed to public access.

3.03 PERFORMANCE

- A. Perform required cutting and patching as required under other Sections of these Specifications.
 1. Perform cutting and demolition by methods which will prevent damage

END OF SECTION

DIVISION 3

CONCRETE

SECTION 03310

CONCRETE REPAIR

PART 1 GENERAL

1.01 RELATED DOCUMENTS

- A. The drawings and general conditions of the contract including General and Supplementary Conditions and other Division 1 Specification sections apply to work of this section.
- B. Examine all other sections of the Specifications for requirements which affect work of this Section whether or not such work is specifically mentioned in this Section.
- C. Coordinate work with that of all trades affecting or affected by work of this Section. Cooperate with such trades to assure the steady progress of all work under the Contract.

1.02 DESCRIPTION OF WORK:

- A. Work included: Provide labor, materials, and equipment necessary to complete the work of this Section and, without limiting the generality thereof, furnish and include the following:
 - 1. The extent of the concrete repair work required to install membrane

1.03 RELATED WORK:

- A. Traffic Coatings: Section 07180
- B. Joint Sealants: Section 07920

1.04 QUALITY ASSURANCE:

- A. Codes and Standards: Comply with provisions of the latest edition of the following except where more stringent requirements are shown or specified:
 - 1.ACI 362.1R-97 "Guide for the Design of Durable Parking Structures."
 - 2.ACI 546R-04 "Concrete Repair Guide."
 - 3.ICRI Technical Guideline No. 03731 "Guide for Selecting Application Methods for the Repair of Concrete Surfaces."

- 4.ICRI Technical Guideline No. 03730 “Guide for Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion”
 - 5.ICRI Technical Guideline No. 03732 “Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays.”
 - 6.“Code of Federal Regulations, Part 1926” per the Occupational Safety and Health Administration (OSHA), Department of Labor (Latest Revision).
- B. Materials and installed work may require testing and retesting, as directed by the Engineer, at any time during progress of work. Allow free access to material stockpiles and facilities. Tests not specifically indicated to be done at Owner's expense, including retesting of rejected materials and installed work, shall be done at Contractor's expense.

1.05 SUBMITTALS

- A. Unless otherwise specified, submittals required in this section shall be submitted for review. Submittals shall be prepared and submitted in accordance with Division 1.
- B. All submittals shall be reviewed and returned to the Contractor within 10 working days.
- C. **Incomplete submittals will not be reviewed.**
- D. Submittals not reviewed by the General Contractor prior to submission to the Engineer will not be reviewed. Include on the submittal statement or stamp of approval by Contractor, representing that the Contractor has seen and examined the submittal and that all requirements listed in this Section and Division 1 have been complied with.
- E. Engineer will review submittals a maximum of two review cycles as part of their normal services. If submittals are incomplete or otherwise unacceptable and re-submitted, General Contractor shall compensate the owner for Engineer’s for additional review(s) cycles.
- F. Product Data: Submit producer’s or manufacturer’s specifications and installation instructions for the following products. Include laboratory test reports and other data to show compliance with specifications (including specified standards).
 - 1.One Component, Early Strength Gaining, Cementitious Repair Material .
 - 2.High Modulus, Low Viscosity, High Strength Epoxy Grout.
 - 3.Admixtures.

4. Primers/Bonding Agents.

G. Contraction/Construction Joints: Reference Section 07920.

1.06 PRODUCT DELIVERY, STORAGE AND HANDLING

- A. Deliver materials to site in manufacturer's original unopened containers and packaging bearing labels as to type and names of products and manufacturers.
- B. Deliver and store restoration material in manufacturer's original, unopened containers with the grade, batch and production data shown on the container or packaging.
- C. Protect restoration material during storage and construction from rain, ground water, and other sources of moisture and from staining or intermixture with soils or other types of material.
- D. Protect grout, mortar and other materials from deterioration by moisture and temperature. Store in a dry location or in waterproof containers. Keep containers tightly closed and away from open flames. Protect liquid components from freezing. Comply with manufacturer's recommendations for minimum and maximum temperature requirements for storage.
- E. Damaged Material: Remove any damaged or contaminated materials from job site immediately, including materials in broken packages or packages containing water marks or other evidence of damage, unless Engineer specifically authorizes correction and use on project.

1.07 PROTECTION/SITE CONDITIONS:

- A. Protect pedestrians, vehicles, building site and surrounding buildings from injury resulting from concrete restoration work.
- B. Clean surfaces only when air temperatures are above 40 degrees F and will remain so until concrete has cured.
- C. Do not perform any patching work if precipitation is expected. In case of unexpected precipitation, work shall cease and all uncured material shall be adequately protected with an impermeable polyethylene sheet.
- D. Do not perform any patching unless the air temperatures are between 40 degrees F and 86 degrees F and will remain a minimum of 40 degrees F for at least 48 hours after completion of work.

- E. If the ambient or subsurface temperature is expected to rise above 86 degrees F during curing then the hot weather requirements of ACI 305R hot weather concreting shall be followed.
- F. If the ambient or subsurface temperature is expected to fall below 40 degrees F during curing then the cold weather requirements of ACI 306R cold weather concreting shall be followed.
- G. Prevent patching materials from staining the face of other surfaces to be exposed to view. Immediately remove all patching materials that come into contact with such surfaces.
- H. Do not apply any material to frozen surfaces.
- I. If materials are installed and cured in temperatures outside of the range noted above or per the manufacturer's recommendations. Written approval and modified installation instructions must be provided from the manufacturer and submitted for record to the Engineer. This installation shall not void the warranty.

PART 2 PRODUCTS

2.01 FORM MATERIALS:

- A. Forms for Exposed Finish Concrete: Unless otherwise indicated, construct formwork for exposed concrete surfaces with plywood, metal, metal-framed plywood faced or other acceptable panel-type materials, to provide continuous, straight, smooth, exposed surfaces. Furnish in largest practicable sizes to minimize number of joints and to conform to joint system shown on drawings. Provide form material with sufficient thickness to withstand pressure of newly-placed concrete without bow or deflection.
- B. Form Coatings: Provide commercial formulation form-coating compounds that will not bond with, stain nor adversely affect concrete surfaces, and will not impair subsequent treatments of concrete surfaces.

2.02 REINFORCING MATERIALS:

- A. Reinforcing Bars: ASTM A 615, Grade 60, deformed and ASTM A 706, Grade 60, deformed, weldable.
- B. Welded Wire Fabric: ASTM A 185, welded steel wire fabric. Provide welded wire fabric in flat sheets.

- C. Supports for Reinforcement: Provide supports for reinforcement including bolsters, chairs, spacers, and other devices for spacing, supporting and fastening reinforcing bars and welded wire fabric in place. Use plastic or wire bar type supports complying with CRSI recommendations, unless otherwise specified. **Wood, concrete block, clay brick and other unspecified devices are not acceptable.**

2.03 REPAIR MATERIALS:

- A. All concrete repair materials shall be compatible with each other and with existing concrete. If possible all primers, repair material, and other products should be from the same manufacturer.
- B. All materials shall be compatible with chloride contents of 1.0 lbs/cy or greater.
- C. All pre-mixed concrete repair products shall be one-component cementitious products specifically noted for use in parking structures.
- D. All materials shall be resistant to stresses resulting from automobile traffic and freeze/thaw cycles, de-icing salts, continuous presence of moisture, and a temperature range of -30 to 100 degrees F.
- E. C.I.P. Topping Repairs.
1. One-component, early strength gaining cementitious repair material with the following properties:
 - a. Minimum 28 day compressive strength: 5000 psi.
 - b. Maximum water cement ratio: 0.40
 - c. Air Content: 6 1/2 +/- 2%
 2. Product shall be recommended for vertical application in parking garages in ACI Exposure Zone III.
 3. Manufacturers:
 - a. Sika
 - b. Masterbuilders
 - c. Sonneborn
 - d. ThoRoc
 - e. Approved equal (must be submitted with bid)

2.04 RELATED MATERIALS:

- A. Moisture-Retaining Cover: One of the following, complying with ANSI/ASTM C 171.
 - 1. Waterproof paper.
 - 2. Polyethylene film.
 - 3. Polyethylene-coated burlap.
- B. Liquid Membrane-Forming Curing Compound: Not permitted.
- C. Preformed Expansion Joint Formers:
 - 1. Bituminous Fiber Type, ASTM D 1751.
 - 2. Felt Void, Poly-Styrene Cap with removable top as manufactured by SUPERIOR.
- D. Slab Joint Filler: Multi-component polyurethane sealant (self-leveling type). Reference Section 07920.

2.05 CONCRETE MIXING:

- A. Mixing shall be in strict conformance with manufacturer's recommendations.

PART 3 EXECUTION

3.01 FORMS:

- A. Design, erect, support, brace and maintain formwork to support vertical and lateral loads that might be applied until such loads can be supported by concrete structure. Construct formwork so concrete members and structures are of correct size, shape, alignment, elevation and position.
- B. Design, construct, erect, maintain, and remove forms for cast-in-place concrete work in compliance with ACI 347.
- C. Design formwork to be readily removable without impact, shock or damage to existing and new concrete surfaces and adjacent materials.
- D. Chamfer exposed corners and edges as indicated or to match existing, using wood, metal, PVC or rubber chamfer strips fabricated to produce uniform smooth lines and tight edge joints.

- E. Cleaning and Tightening: Thoroughly clean forms and adjacent surfaces to receive concrete. Remove chips, wood, sawdust, dirt or other debris just before concrete is placed. Retighten forms and bracing after concrete placement as required to eliminate mortar leaks and maintain proper alignment.

3.02 PLACING REINFORCEMENT:

- A. Comply with Concrete Reinforcing Steel Institute's recommended practice for "Placing Reinforcing Bars", for details and methods of reinforcement placement and supports, and as herein specified.
 - 1. Clean reinforcement of loose rust and mill scale, earth, ice, and other materials which reduce or destroy bond with concrete.
 - 2. Accurately position, support and secure reinforcement against displacement by formwork, construction, or concrete placement operations. Locate and support reinforcing by metal chairs, runners, bolsters, spacers and hangers, as required.
 - 3. Install welded wire fabric in flat sheets in as long lengths as practicable. Lap adjoining pieces at least two full mesh and lace splices with wire. Offset end laps in adjacent widths to prevent continuous laps in either direction.

3.03 PREPARATION OF FORM SURFACES

- A. Prior to patching, all surfaces must be prepared in accordance with this section of the specification and the manufacturers recommendations.
- B. Sawcut perimeter of damage area to a depth of 1/2" +/- (unless note otherwise on Drawings). Do not cut reinforcement. Remove, by hand, a section to confirm depth of reinforcement and adjust depth as required.
- C. The removal of all unsound concrete, using lightweight demolition hammers, not to exceed **15 pounds is recommended**. All removals to be performed with ICRI Guidelines, which shall be a part of these specifications, with regard to removal geometry, exposure, undercutting and cleaning of embedded reinforcement, and conditioning of edges and surfaces. **Damage caused as a result of using larger hammers will be repaired at the Contractors expense.**
- D. Steel reinforcement shall be thoroughly prepared by mechanical cleaning to remove all traces of rust.
- E. Pressure wash all surfaces, including reinforcement using 3000 to 4000 psi water blast, as required to remove all dust and dirt. The surface shall be saturate surface dry (SSD) with no standing water during application

- F. The result of this preparation shall render an exposed aggregate surface with a minimum surface profile of +/- 1/8". The surface shall be clean, meaning having complete exposure of sound original material without any deposits of contaminants, foreign matter or loose material, which could affect the bond or long term durability of the surface and the repair material.

3.04 INSPECTION:

- A. Inspect all concrete surfaces prior to application of primers/adhesives to insure proper preparation and surface drying.
- B. Conform to all manufacturers' preparation instructions.
- C. Inspect reinforcement for section loss at locations of deterioration. If loss exceeds 25% notify Engineer prior to proceeding with the repair.

3.05 PRIMING OF REINFORCING STEEL

- A. Any reinforcement exposed in the course of removing unsound materials shall be cleaned and prepared in accordance with the above specifications.
- B. All exposed reinforcement shall be primed with an approved bonding agent compatible with the repair materials. Coat all exposed surfaces in accordance with the manufacturer's instructions. Care must be taken to create a continuous coating on the full surface, including the underside of the undercut reinforcement. Observe manufacturer's minimum and maximum timing window for repair after application of primer.

3.06 CONCRETE REPAIR

- A. Following preparation, as specified above, contractor shall maintain work area in a clean condition, including materials, equipment and workers' footwear, to avoid tracking in of contaminants, dirt, dust, mud or other materials which may interfere with adhesion and durability of repairs.
- B. Prior to installation, all repair areas shall be kept continuously wet for at least 20 minutes prior to application of patching compound. Before placing repair material, excess water shall be blown, vacuumed or otherwise removed from the surface, leaving the surface damp or saturated/surface dry.

- C. Vigorously brush apply a thin primer coat of acrylic latex bonding agent with added 10% neat Type 1 portland cement into all cavity surfaces. Unless noted otherwise in manufacturer's installation instructions. All primers shall be compatible with repair material.
- D. Within specified time frame of primer application, mix and place repair compound in accordance with manufacturer's instructions.
- E. Mix the precisely measured quantity of water specified by the manufacturer with full bags of patching compound only. Mix using slow speed drill (450 rpm maximum) with mud or paddle mixer. Motorized mortar mixers may be used for mixing larger quantities. Mix to a uniform consistency, free of lumps or dry material. Do not whip air into the mix. Do not overmix
- F. When placing the repair material, care shall be taken to assure that all corners and gaps under reinforcing steel and entire cavity profile is completely filled and properly compacted to prevent formation of voids or unbonded areas. "Work" the material into corners and gaps, and onto cavity sidewalls using pressure on the trowel to assure good contact between patch and substrates.
- G. Patches deeper than 1" (25 mm) may be extended by coarse aggregate addition. 20 pounds of clean, washed, 3/8" pea stone suitable in composition and surface profile for use as a concrete aggregate, may be added to each 50 pound bag of patching compound.
- H. Do not re-temper material which has begun to set. Discard any unused material after 20 minutes. Do not excessively wet repair surfaces after placement or as an aid to trowelling. Limit surface water addition to light misting and do not wet or rework repeatedly.
- I. Observe the curing requirements for each day's working conditions, as specified herein. Do not open to traffic or expose to weather until adequate strength has been reached, as affected by working and curing conditions.
- J. Finish: Provide finish to match existing or as required for membrane application.

3.07 CRACK REPAIR:

- A. Preparation:
 - 1. Remove all existing joint sealant.
 - 2. Center routed groove on crack.
 - 3. Remove all loose and deteriorated material.

4. All joint wall surfaces must be clean, sound, and frost free. Joint walls must be free of oils, grease, curing compound residues, and any other foreign matter that might prevent bond. This should be accomplished by blast cleaning or equivalent mechanical means.

5. Conform to all manufacturers' preparation requirements.

B. Sealant Installation:

1. Sealant shall conform to specification Section 07920; Joint Sealant.
2. Install as per manufacturer's requirements.
3. Install sealant evenly and recess 1/8" below surface. DO NOT OVERFILL JOINT.

3.08 MONOLITHIC REPAIR FINISHES:

- A. Float Finish: Apply float finish to monolithic slab surfaces to receive trowel finish and other finishes as hereinafter specified, and slab surfaces which are to be covered with membrane or elastic waterproofing, and as otherwise indicated.
- B. Trowel Finish: Apply trowel finish to monolithic slab surfaces indicated, including slab surfaces to be covered with carpet, resilient flooring, paint or other thin-film finish coating system.
- C. Slab finishes for floor coverings not indicated shall be coordinated with the Engineer prior to slab placement.

3.09 CONCRETE CURING AND PROTECTION:

- A. General: Protect freshly placed concrete from premature drying and excessive cold or hot temperatures. Protect concrete work from physical damage or reduced strength which could be caused by frost, freezing actions, or low temperatures, in compliance with the requirements of ACI 306 as herein specified.
- B. Curing Methods: Perform curing of concrete by moist curing, by moisture-retaining cover curing. **Slab repairs shall be cured by moist curing methods for a minimum of 3 days.**
- C. Protection From Mechanical Injury: During the curing period, the concrete shall be protected from damaging mechanical disturbances, such as load stresses, heavy shock, and excessive vibration. All finished concrete surfaces shall be protected from damage by construction equipment, materials, or methods, by application of curing procedures, and by rain or running water. Self-supporting structures shall not be loaded in such a way as to overstress the concrete.

3.10 QUALITY CONTROL TESTING DURING CONSTRUCTION:

- A. Engineer shall verify reinforcement, including slab reinforcement (WWF or reinforcing bar).
- B. Concrete shall be sampled and tested for quality control during placement. Quality control testing shall include the items listed in paragraph D, this section, unless otherwise directed by the Engineer.

3.11 CLEANING:

- A. Clean off excess material adjacent to work in progress by methods and with cleaning materials approved by manufacturer of patch materials.

END OF SECTION

DIVISION 5

METALS

SECTION 05120

STRUCTURAL STEEL

PART 1 GENERAL

1.01 RELATED DOCUMENTS

- A. The drawings and general conditions of the contract including General and Supplementary Conditions and other Division 1 Specification sections apply to work of this section.
- B. Examine all other sections of the Specifications for requirements which affect work of this Section whether or not such work is specifically mentioned in this Section.
- C. Coordinate work with that of all trades affecting or affected by work of this Section. Cooperate with such trades to assure the steady progress of all work under the Contract.

1.02 DESCRIPTION OF WORK:

- A. Extent of structural steel work is shown on drawings, including removal of four existing beams and installation of four new beams using existing connections.
- B. Structural steel is that work defined in AISC “Code of Standard Practice” and as otherwise shown on drawings.

1.03 QUALITY ASSURANCE:

- A. Codes and Standards: Comply with latest provisions of the following, except as otherwise indicated:
 - 1. AISC “Code of Standard Practice for Steel Buildings and Bridges”, Latest Edition.
 - a. The provisions of Section 10, “Architecturally Exposed Structural Steel”, apply to exposed steel elements for this project. In addition, exposed welds shall be ground to provide smooth surface.
 - b. Exclude the word “structural” in reference to the “Design Drawings” in section 3.1 of the Code.
 - 2. AISC “Specification for Structural Steel Buildings”, including “Commentary” and Supplements issued thereto.

3. AISC “*Specifications for Structural Joints using ASTM A 325 or A 490 Bolts*” approved by the Research Council on Structural Connections of the Engineering Foundation.
 4. AWS D1.1 - “Structural Welding Code” - Steel.
 5. AWS D1.3 - “Structural Welding Code” - Sheet Steel.
 6. ASTM A6 “General Requirements for Delivery of Rolled Steel Plates, Shapes, Sheet Piling and Bars for Structural Use.”
 7. “Code of Federal Regulations, Part 1926” per the Occupational Safety and Health Administration (OSHA), Department of Labor (Latest Revision).
- B. Qualifications for Welding Work: Qualify welding processes and welding operators in accordance with AWS D1.1 “Standard Qualification Procedure.”
1. Provide certification that welders to be employed in work have satisfactorily passed AWS D1.1 qualification tests and maintained a current certification. Current certification and/or continuity log shall be submitted and be available in the field.
 2. If re-certification of welders is required, retesting will be the Contractor’s responsibility.
- C. Fabricator Qualifications: N/A.
- D. Paint Endorsement: N/A.

1.04 SUBMITTALS

- A. Unless otherwise specified, submittals required in this section shall be submitted for review. Submittals shall be prepared and submitted in accordance with this section and 01300.
- B. All submittals shall be reviewed and returned to the contractor within 10 working days.
- C. INCOMPLETE SUBMITTALS WILL NOT BE REVIEWED.**
- D. Submittals not reviewed by the General Contractor prior to submission to the Engineer will not be reviewed. Include on the submittal statement or stamp of approval by Contractor, representing that the Contractor has seen and examined the submittal and that all requirements listed in Division 1 have been complied with.

- E. Engineer will review submittals a maximum of two review cycles as part of their normal services. If submittals are incomplete or otherwise unacceptable and re-submitted, General Contractor shall compensate Engineer for additional review cycles.
 - F. Hardcopy Submittals: Submit three prints. Prints will be reviewed by the Engineer. One marked print will be returned to Contractor for printing and distribution. Multiple copies will not be marked by the Engineer.
 - G. Product Data: Submit producer's or manufacturer's specifications and installation instructions for the following products. Include laboratory test reports and other data to show compliance with specifications (including specified standards).
 - 1. Structural steel certified mill reports for each grade of steel covering chemical and physical properties and yield strengths.
 - 2. High-strength bolts (each type), including nuts and washers.
 - 3. Structural steel primer paint.
 - 4. Structural steel top coat paint or add painting into this specification.
 - H. Shop Drawings:
 - 1. Shop Drawing Review: Electronic files of structural drawings will not be provided to the contractor for preparation of shop drawings. Reproduction of any portion of the Construction Documents for use as Shop drawings and/or Erection Drawings is prohibited. Shop drawings and/or Erection drawings created from reproduced Construction Documents will be returned without review.
 - a. Review of the shop drawings will be made for the size and arrangement of the members and strength of the connections. Conformance of the Shop Drawings to the Contract Drawings remains the responsibility of the General Contractor. Engineer's review in no way relieves the General Contractor of this responsibility.
 - b. Shop drawings will not be reviewed as partial submittals. A complete submittal shall be provided and shall include; erection and piece drawings indicating all members, braced frames, moment frames and connections. Incomplete submittals will not be reviewed.
- 1.05 DELIVERY, STORAGE AND HANDLING:
- A. Deliver materials to site at such intervals to insure uninterrupted progress of work.

- B. Store materials to permit easy access for inspection and identification. Keep steel members off ground, using pallets, platforms, or other supports. Protect steel members and packaged materials from corrosion and deterioration.
- C. Do not store materials on structure in a manner that might cause distortion or damage to members or supporting structures. Steel materials shall be stored in a manner to avoid ponding of precipitation on members. Repair or replace damaged materials or structures as directed.

PART 2 PRODUCTS

2.01 MATERIALS:

- A. Structural Steel Shapes, Plates and Bars (U.N.O): ASTM A 36 minimum, higher strength steel is acceptable.
- B. Structural Steel Hot Rolled Wide Flange Shapes: ASTM A 992 Grade 50 (ASTM A572 Grade 50 with special requirements per AISC Technical Bulletin #3, dated March 1997)
- C. Unfinished Threaded Fasteners: ASTM A 307, Grade A, regular low-carbon steel bolts and nuts. Provide hexagonal heads and nuts for all connections.
- D. Electrodes for Welding:
 - 1. Minimum 70 ksi electrodes. Filler material shall meet the grouping requirements per AWS D1.1 Table 3.1 for matching strength of connected materials.
 - 2. All filler metal used welding shall meet the following Charpy V-Notch (CVN) requirements.
 - a. 20 ft-lb at 0 degrees Fahrenheit unless noted otherwise.
 - b. 20 ft-lb at -20 degrees Fahrenheit and 40 ft-lb at 70 degrees Fahrenheit at all complete joint penetration (CJP) groove welds.
- E. Structural Steel Coatings shall be as specified in the Structural Steel Coatings section of this specification, and as specified in Division 9.

2.02 FABRICATION:

- A. Shop Fabrication and Assembly: Fabricate and assemble structural assemblies in shop to greatest extent possible. Fabricate items of structural steel in accordance with AISC Specifications and as indicated on final shop drawings.

1. Properly mark and match-mark materials for field assembly. Fabricate for delivery sequence which will expedite erection and minimize field handling of materials.
 2. Where finishing is required, complete assembly, including welding of units, before start of finishing operations. Provide finish surfaces of members exposed in final structure free of markings, burrs and other defects.
- B. Connections: Weld or bolt shop connections, as indicated.
1. Provide field bolted connections, except where welded connections or other connections are indicated.
 2. Provide high-strength threaded fasteners for principal bolted connections, except where unfinished bolts are indicated.
- C. High-Strength Bolted Connection: Install high-strength threaded fasteners in accordance with AISC “Specification for Structural Joints using ASTM A 325 or A 490 Bolts”. Unless otherwise indicated, all bolted connections are to be tightened to the snug tight condition as defined by AISC.
- D. Welded Construction: Comply with AWS Codes for procedures, appearance and quality of welds, and methods used in correcting welding work.
- E. Holes for Other Work: Provide holes required for securing other work to structural steel framing, and for passage of other work through steel framing members, as shown on final shop drawings.
- F. Cut, drill, or punch holes perpendicular to metal surfaces. Do not flame cut holes or enlarge holes by burning. Drill holes in bearing plates.
- G. Fabricator, Erector and General Contractor shall coordinate safety requirements for the project, in accordance with OSHA Part 1926. Provide all necessary pieces and fabrications as required to safely erect and access the structure for the duration of project construction.

2.03 STRUCTURAL STEEL COATINGS

- A. Coordinate coating requirements with Division 9 of the specifications.
- B. To the greatest extent possible, structural steel coatings shall be shop applied.
- C. Galvanizing, priming and painting for structural steel permanently exposed to view shall meet the requirements of Section 10 of the Code of Standard Practice, “Architecturally Exposed Structural Steel”.

- D. Follow manufacturer's installation and safety instructions when applying coatings. Adhere to recoat time recommendations set forth by manufacturer.
- E. General: Shop priming of structural steel is not required for heated, interior steel not exposed to view unless noted otherwise.
- F. Coatings: All exterior steel and/or steel permanently exposed to view shall receive a coating. Unless noted otherwise, refer to Division 9 specifications for products and surface preparation requirements.
- G. Unheated structural steel to be enclosed with architectural finishes, including but not by limitation, canopy members and/or roof pop-up members shall be primed with rust inhibitive alkyd primer, Tnemec Series 349 unless noted otherwise. Follow manufacturer's instructions for surface preparation and application. Substitution shall be equal to the above specified products, and shall be submitted for review.
- H. Field Touch-up: Touch-up all paint and galvanizing damage, including but not by limitation, damage caused during shipping, erection, construction damage, and field welded steel. See Division 9 specifications for additional requirements.

PART 3 EXECUTION

3.01 ERECTION:

- A. General: Comply with AISC Specifications for bearing, adequacy of temporary connections, alignment, and removal of paint on surfaces adjacent to field welds.
- B. Erection Procedures: Comply with "Code of Federal Regulations, Part 1926" per the Occupational Safety and Health Administration (OSHA), Department of Labor (Latest Revision).
- C. Temporary Shoring and Bracing: This is the sole responsibility of the Contractor. Provide temporary shoring and bracing members with connections of sufficient strength to support imposed loads. Remove temporary members and connections when all permanent members are in place, and all final connections are made, including the floor and roof diaphragms. Provide temporary guy lines to achieve proper alignment of structures as erection proceeds. Comply with OSHA Standard referenced previous. Retain the services of a Specialty Structural Engineer (Not the Engineer of Record) to design specialty shoring and bracing.
- D. Field Assembly:
 - 1. Set structural members accurately to lines and elevations indicated.

2. Align, adjust, level and plumb members of complete frame in to the tolerances indicated in the AISC Code of Standard Practice and in accordance with OSHA regulations.
 3. Clean bearing surfaces and other surfaces which will be in permanent contact before assembly.
 4. Perform necessary adjustments to compensate for discrepancies in elevations and alignment.
 5. Do not enlarge unfair holes in members by burning or by use of drift pins, except in secondary bracing members. Ream holes that must be enlarged to admit bolts.
- E. Erection bolts: Remove erection bolts. On exposed welded construction and at all braced frame members fill holes with plug welds and grind smooth at exposed surface.
- F. Gas Cutting: Do not use gas cutting torches in field for correcting fabrication errors in primary structural framing. Cutting will be permitted only on secondary members which are not under stress, as accepted by the Engineer of Record. Finish gas-cut sections equal to a sheared appearance when permitted.
- G. Coating Damage: Touch up shop applied paint or galvanizing whenever damaged or bare. See "Coatings" sections for additional requirements.
- H. Field Cut Beam Web Penetrations:
1. Field cut beam web penetrations are not permitted.
- I. Welders shall have current evidence of passing and maintaining the AWS D1.1 Qualifications test available in the field.
- J. Welding electrodes, welding process, minimum preheat and interpass temperatures shall be in accordance with AISC and AWS specifications. Any structural steel damaged in welding shall be replaced.
- 3.02 QUALITY CONTROL:
- A. General: Contractor is responsible for maintaining quality control in the field and for providing a structure that is in strict compliance with the Contract Documents.
1. Required inspection intended to assist the Contractor in complying with the Contract Documents. These specified services, however, do not relieve the Contractor of his responsibility for compliance, nor are they intended to limit the Contractor's quality control efforts in the field.

- B. Nonconforming Work: Contractor shall be responsible for correcting deficiencies in structural steel work which inspections laboratory test reports have indicated to be not in compliance with requirements. Additional tests and/or surveys shall be performed, at the Contractor's expense, as may be necessary to show compliance of corrected work. Any costs associated with the Engineer's review and disposition of faulty works shall be borne by the Contractor.

END OF SECTION

DIVISION 7

THERMAL AND MOISTURE PROTECTION

SECTION 07180

TRAFFIC COATINGS

PART 1 GENERAL

1.01 SUMMARY

- A. The drawings and general conditions of the contract apply to work of this section.
- B. Examine all other sections of the Specifications for requirements which affect work of this Section whether or not such work is specifically mentioned in this Section.
- C. Coordinate work with that of all trades affecting or affected by work of this Section. Cooperate with such trades to assure the steady progress of all work under the Contract.
- D. The work described in this section will proceed while garage operations continue. Contractor to coordinate traffic patterns with garage manager for garage to remain open to traffic during construction. Contact information for garage manager will be provided after the award of the contract.
- E. There will be parking spaces made available to the contractor Monday through Sunday for the work and traffic alterations at any one time during construction. Contractor to provide all traffic barriers signage, and traffic flagging personnel as required to maintain safe garage operation during construction. **Security and flagging personnel are mandatory if two-way traffic is required on any ramp.**
- F. Contractor's Use of Premises: During construction, Contractor shall have restricted use of the garage as described within the specifications. Contractor's use of premises is limited only by Owner's right to perform work or employ other contractors on these premises.

1.02 DESCRIPTION OF WORK

- A. Furnish all the labor, materials, equipment, and incidentals necessary to coat the levels indicated on the drawings. Coat these locations with NEOGARD AUTO-GARD® FC or NEOGARD AUTO-GARD® EAS where surfaces have been previously coated with a membrane (approximately 9,600 sf, 1,000 sf Heavy Duty, 8,600 Medium Duty). Preparation, application and clean up are per these specifications and manufacturers recommendations. This work shall include restriping of parking spaces and painting of directional information to match existing layout and a five (5) year Joint and Several (material and labor) warranty.

- B. Contractor shall specify which product they intend to use in the bid package. No substitutions will be considered after the bids have been opened unless it is determined to be a benefit to the owner.
 - C. All existing membrane that is loose or not fully adhered shall be completely removed to concrete.
 - D. The traffic membrane system shall be a complete system of compatible materials supplied by NEOGARD[®] to create a seamless waterproof membrane.
- 1.03 RELATED SECTIONS
- A. Section 01300 SUBMITTALS
 - B. Section 01500 CONSTRUCTION FACILITIES AND TEMPORARY CONTROLS
 - C. Section 01710 CLEANING
 - D. Section 03310 CAST-IN-PLACE CONCRETE REPAIR
 - E. Section 07920 JOINT SEALANTS
- 1.04 SUBMITTALS
- A. Unless otherwise specified, submittals required in this section shall be submitted for review. Submittals shall be prepared and submitted in accordance with Section 01300.
 - B. All submittals shall be reviewed and returned within 10 working days.
 - C. Incomplete submittals will not be reviewed.
 - D. Submittals not reviewed by the Contractor prior to submission to the Engineer will not be reviewed. Include on the submittal statement or stamp of approval by Contractor, representing that the Contractor has seen and examined the submittal and that all requirements listed in this Section and Section 01300 have been complied with.
 - E. Engineer will review submittals a maximum of two review cycles as part of their normal services. **If submittals are incomplete or otherwise unacceptable and re-submitted, General Contractor shall compensate the Owner for additional review cycles.**
 - F. Product Data: Submit manufacturer's specifications and installation instructions for the following products. Include laboratory test reports and other data to show compliance with specifications (including specified standards).

1. NEOGARD AUTO-GARD® FC or NEOGARD AUTO-GARD® EAS Traffic-Bearing Membrane System
2. Warranty: Submit a sample warranty that states that the material and labor/workmanship involved in this application will be warranted for 5 years from the date of substantial completion by the installer and NEOGARD®.
3. **Applicator's Approval: Submit a currently dated letter from NEOGARD® Division of JONES-BLAIR® stating applicator is approved to install vehicular traffic coating system specified in full compliance with the material warranty.**
4. No substitutions will be considered.

1.05 QUALITY ASSURANCE

- A. Codes and Standards: Comply with provisions of the following, except as otherwise indicated:
1. ICRI Guidelines No. 03732 "Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays."
 2. "Code of Federal Regulations, Part 1926" per the Occupational Safety and Health Administration (OSHA), Department of Labor (Latest Revision).
 3. ACI 308: Standard Practice for Curing Concrete
 4. Neogard Construction Products, "Recoat Guidelines Standard & Fast-Cure Coating Systems", www.neogard.com.
- B. Manufacturer qualifications: Auto-Gard® FC and EAS as supplied by NEOGARD® is approved for use on this project.
- C. Contractor qualifications: Qualified to perform work specified by reason of experience or training provided by product manufacturer.
- D. Mockup: Provide mockup of at least 25 square feet to include surface preparation/profile, for each condition and allow for evaluation of slip resistance of Traffic Deck Coating System and adhesion test in accordance with ASTM D4541.
1. Install mockup with specified coating types and with other components noted.
 2. Locate where directed by Engineer or Owner.
 3. Mockup may remain as part of Work if acceptable to Engineer and Owner.

- E. Notify manufacturer's authorized representative at least two weeks before start of work. Schedule minimum of 2 job site inspections by manufacturer's authorized representative, first scheduled before application of product to review surface preparation for each condition. Second, to review application/installation of membrane systems at each condition. **Application of elastomeric Traffic Deck Coating System without prior review by manufacturer will not void the warranty provided to the Owner.**
- 1.06 DELIVERY, STORAGE, AND HANDLING
- A. Deliver products in original sealed factory packaging bearing identification of product, manufacturer, and batch number. Provide Material Safety Data Sheets for each product.
- B. Store product in location protected from freezing, damage, construction activity, precipitation, and direct sunlight, in strict accordance with manufacturer's recommendations.
- C. Recommended storage temperature is 75 degrees F.
- D. Handle all products with appropriate precautions and care as stated on Material Safety Data Sheet.
- 1.07 PROJECT CONDITIONS
- A. Do not use products under conditions of precipitation or freezing weather or when such conditions are imminent. Use appropriate measures for protection and supplementary heating to ensure proper drying and curing conditions in accordance with manufacturer's recommendations if application during inclement weather occurs.
- B. Ensure substrate is clean and dry prior to application.
- C. **Do not proceed with application of materials when deck temperature is less than 40 degrees F unless approved in writing by the manufacturer.**
- D. Protect all adjacent work from contamination due to mixing, handling, and application of preparation and repair products and Traffic Deck Coating System.
- E. Conform to all the manufacturer's recommendations regarding project/surface conditions.

PART 2 PRODUCTS

2.01 MANUFACTURERS

A. The only acceptable manufacturer and supplier allowed under this section is NEOGARD® Division of JONES-BLAIR® Company, P.O. Box 35286, Dallas, TX 75235, Toll Free (800) 321-6588, Fax (214) 357-7532, www.neogard.com.

2.02 PERFORMANCE CRITERIA

A. Compliance: ASTM C957

B. Physical properties of cured vehicular traffic coating system used on this project are:

PERFORMANCE REQUIREMENTS OF CURED FILM			
PHYSICAL PROPERTIES	TEST METHOD	BASE COAT	TOPCOAT
Tensile Strength	ASTM D412	1,500 psi	2,200-5,000 psi
Elongation	ASTM D412	500%	80-350%
Permanent Set	ASTM D412	<20%	<20%
Tear Resistance	ASTM D1004	150 pli	165-400 pli
Water Resistance	ASTM D471	1% @ 7 days	<=3% @ 7 days
MVT @ 20 mils	ASTM E96	5 English	0.4-1.5 English
Taber Abrasion (cs17), max	ASTM D4060	5 mg/1,000 rev	30 mg/1,000 rev
Shore A	ASTM D2240	74-79	84-94
Adhesion	ASTM D4541	400 psi	400 psi
Weathering Resistance	ASTM D822	N/A	Slight Chalk
Thermal Shock	Alternate Heat/Cold	No Loss of Adhesion	No Loss of Adhesion
"Standard Specifications for High Solids Content, Cold- Applied Elastomeric Waterproofing Membrane with Integral Wearing Surface"	ASTM C957	System Exceeds Requirements	

2.03 MATERIALS

A. Vehicular Traffic Coating Material

1. Primer: Concrete and metal primers as required by NEOGARD®.
2. Flashing Tape: 86218 flashing tape (ETERNABOND™ WebSeal™) or approved equal having a minimum thickness of 30 mils.
3. Liquid Flashing: FC7500/FC7960 or FC7520/FC7962 polyurethane coating.

4. Sheet Flashing: 6” wide or 12” wide UltraGard EPDM flashing manufactured by John Manville or equal non-staining elastomeric sheet flashing having a min thickness of 60 mils.
 5. Aggregate: 7992T silica (quartz) sand or other aggregate approved by NEOGARD®.
 6. Elastomeric Base Coat: FC7500/FC7960 polyurethane coating, gray in color.
 7. Elastomeric Topcoat (Interior or Covered Use Only): FC7510/FC7961 series polyurethane coating.
 8. Elastomeric Topcoat (Exterior/Interior Use): FC7520/FC7962 series polyurethane coating.
 9. Sealant: Polyurethane sealant approved by NEOGARD®.
- B. Match as close as possible to existing colors.

PART 3 EXECUTION

3.01 EXAMINATION

- A. Inspect all areas involved in work to establish extent of work, access and need for protection of surrounding construction.
- B. Protect all surroundings from Primers, Patching Repair Compounds and Finish products and to include, but not be limited to, windows, roofs, walkways, drives, automobiles, and landscaping.
- C. Existing Concrete Decks: Verify that the work done under other sections meets the following requirements:
 1. That the concrete deck surface is free of ridges and sharp projections.
 2. That the concrete was cured for a minimum of 28 days. (Minimum of 5,000 psi compressive strength). Water-cured treatment of concrete is preferred. The use of concrete curing agents require written approval by NEOGARD®.
 3. That the concrete was finished by a power or hand steel trowel followed by soft hair broom to obtain light texture or “sidewalk” finish.
 4. That damaged areas of the concrete deck be restored to match adjacent areas.

D. Existing Membrane

1. Review all existing areas of membrane and ensure that all loose/deteriorated areas are completely removed to concrete. **Any existing membrane left in place, to be coated over, must be fully adhered to the substrate.**

3.02 SITE VERIFICATIONS OF CONDITIONS

- A. Conduct all pre-application inspections of site verification with authorized Manufacturer's Representative.
- B. Inspect all joints to ensure there is no deteriorated sealant, adhesion loss or non-elastomeric caulks installed in joints. Repair all deficient sealant.
- C. Inspect all through deck penetrations, including electrical, lighting, signage, plumbing, HVAC, fire sprinkler piping for watertight seal. Repair all deficiencies.

3.03 SURFACE PREPARATION:

A. NEW & EXISTING CONCRETE SURFACES:

1. **Cleaning:** Surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong non-sudsing detergent. Thoroughly wash, clean, and dry. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods.
2. **Shot Blasting:** Required surface preparation method for remedial construction, is also the preferred method for new construction. Mechanically prepare surface by shot blasting to industry standard surface texture (ICRI's CSP3-4) without causing additional surface defects in deck surface. Shot blasting does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the deck coating.
3. **Cracks and Cold Joints:** Visible hairline cracks (up to 1/16" in width) in concrete and cold joints shall be cleaned, primed as required and treated with liquid flashing a minimum distance of 2" on each side of crack to yield a total thickness of 30 dry mils. Large cracks (over 1/16" in width) shall be routed and sealed with sealant. Sealant shall be applied to inside area of crack only, not applied to deck surface. Detail sealed cracks with liquid flashing a distance of 2" on each side of crack to yield a total thickness of 30 dry mils.
4. **Control Joints:** Seal secondary control joints with sealant. Sealant shall be applied to inside area of joint only, not applied to deck surface. Detail sealed joints with liquid flashing a distance of 2" on each side of joint to yield a total thickness of 30 dry mils.

5. Flashing Tape: Install flashing tape where recommended by manufacturer prior to the application of elastomeric coating.
6. Surface Condition: Surface shall be clean and dry prior to coating.

B. EXISTING MEMBRANE

1. Remove all existing surface applied membrane material that is loose or marginally bonded.
2. Check all exposed concrete surfaces for defects and repair in accordance with section 03310.
3. Clean existing deck coatings by power washing, (600 to 800 psi), with trisodium phosphate or other non-sudsing detergent. The use of stiff bristle brooms may be required to help remove some contaminants. Rinse decks thoroughly and clean potable water and allow to dry completely. All low spots where water puddles must be vacuumed dry to remove any contaminants left by the rinsing operation.
4. Existing Membrane surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong non-sudsing detergent. Thoroughly wash, clean, and dry.

3.04 APPLICATION:

A. NEW & EXISTING CONCRETE SURFACES:

1. Complete all preparatory work before application begins. Apply base coat, intermediate, and top coats with properly sized equipment to arrive at required mil thickness. Verify mil thickness of all coats by use of wet-mil thickness gauge.
2. Vacuum thoroughly all surfaces to be coated. Apply primer to all deck surfaces at manufacturers recommended application rate. Force primer into pores and voids to eliminate pinholes. Do not apply Primer over pre-stripping.
3. **The application of this product by the “Seed and Back Roll” method is not allowed on this project.**
4. Installation: **NEOGARD AUTO-GARD FC**
 - a. **Primer:** Apply 7795/7796 primer at a rate of 300-500 sf/gallon to all exposed concrete and coated surfaces in strict accordance with

procedures outlined by NEOGARD®. **Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, re-prime.**

- b. **Base Coat:** Apply FC7500/7960 to concrete surfaces at a rate of 80 sf/gallon (20 mils) in strict accordance with procedures outlined by NEOGARD®. Extend base coat over cracks and control joints which have received treatment.
 - c. **Wearing Surface Coat for Medium Duty Applications:** Apply FC7510/7961 coat at a rate of 100 sf/gallon (8 mils) in strict accordance with procedures outlined by NEOGARD® and immediately broadcast **7992T aggregate**, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet.
 - d. **Additional Wearing Surface Coat for Heavy Duty (Turn Areas) Applications:** At all turn areas noted on drawings, apply double-texture as follows: After the wearing surface coat to receive aggregate has cured and loose aggregate removed, apply FC7510/7961 at a rate of 133 sf/gallon (12 mils) strict accordance with procedures outlined by NEOGARD® and immediately broadcast additional **7992T aggregate**, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet.
 - e. **Finish Top Coat:** When dry, remove excess aggregate and recoat surface with FC7510/7961 at rate of 133sf/gallon (16 mils) in strict accordance with procedures outlined by NEOGARD®.
 - f. Total system coating thickness averages 40 dry mils exclusive of aggregate. Double-textured turn areas will yield an average of 52 dry mils exclusive of aggregate.
5. Installation: **NEOGARD AUTO-GARD EAS**
- a. **Primer:** Apply 7795/7796 primer at a rate of 300-500 sf/gallon to all exposed concrete and coated surfaces in strict accordance with procedures outlined by NEOGARD®. **Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, re-prime.**
 - b. **Base Coat:** Apply FC7500/7960 to concrete surfaces at a rate of 80 sf/gallon (20 mils) in strict accordance with procedures outlined by NEOGARD®. Extend base coat over cracks and control joints which have received treatment.

- c. **Wearing Surface Coat for Medium Duty Applications:** Mix elastomeric topcoat material FC7510/7961 for 3 to 5 minutes. Once mixed, add aggregate **7992T aggregate** at the rate of 10lbs/gallon and mix until thoroughly blended. Immediately place coatings/aggregate mix and spread with ¼” notched squeegee. Note: Depending on amount of time between mixing aggregate and placement of coating/aggregate mix, it may be necessary to agitate mix to suspend aggregate before placing. Apply coating/aggregate mix at a rate of 1.25 gallons per 100 square feet (80sf/gal) to yield and average of 20 dry mils. Use 18 inch wide 5/8 inch nap roller to even out mix and apply final finish. Care must be taken to roll out “heavy” accumulations of coating. The total Medium Duty system will yield an average of 40 dry mils.
- d. **Wearing Surface Coat for Heavy Duty (Turn Areas) Applications:** Mix elastomeric topcoat material FC7510/7961 for 3 to 5 minutes. Once mixed, add aggregate **7992T aggregate** at the rate of 10 lbs/gallon and mix until thoroughly blended. Immediately place coatings/aggregate mix and spread with ¼” notched squeegee. Note: Depending on amount of time between mixing aggregate and placement of coating/aggregate mix, it may be necessary to agitate mix to suspend aggregate before placing. Apply coating/aggregate mix at a rate of 2 gallons per 100 square feet (50sf/gal) to yield and average of 32 dry mils. Use 18 inch wide 5/8 inch nap roller to even out mix and apply final finish. Care must be taken to roll out “heavy” accumulations of coating. The total Heavy Duty system will yield an average of 52 dry mils.
4. Installation: **NEOGARD AUTO-GARD EAS**
- a. **Primer:** Apply 7795/7796 primer at a rate of 300-500 sf/gallon to all exposed concrete and coated surfaces in strict accordance with procedures outlined by NEOGARD®. **Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, re-prime.**
- b. **Wearing Surface Coat for Medium Duty Applications:** Mix elastomeric topcoat material FC7510/7961 for 3 to 5 minutes. Once mixed, add aggregate **7992T aggregate** at the rate of 10lbs/gallon and mix until thoroughly blended. Immediately place coatings/aggregate mix and spread with ¼” notched squeegee. Note: Depending on amount of time between mixing aggregate and placement of coating/aggregate mix, it may be necessary to agitate mix to suspend aggregate before placing. Apply coating/aggregate mix at a rate of 1.25 gallons per 100 square feet (80sf/gal) to yield and average of 20 dry mils. Use 18 inch wide 5/8 inch nap roller to even out mix and apply final finish. Care must be taken to

roll out “heavy” accumulations of coating. Medium Duty system will yield an average of 20 dry mils over existing membrane.

- c. **Wearing Surface Coat for Heavy Duty (Turn Areas) Applications:** Mix elastomeric topcoat material FC7510/7961 for 3 to 5 minutes. Once mixed, add aggregate **7992T aggregate** at the rate of 10 lbs/gallon and mix until thoroughly blended. Immediately place coatings/aggregate mix and spread with ¼” notched squeegee. Note: Depending on amount of time between mixing aggregate and placement of coating/aggregate mix, it may be necessary to agitate mix to suspend aggregate before placing. Apply coating/aggregate mix at a rate of 2 gallons per 100 square feet (50sf/gal) to yield an average of 32 dry mils. Use 18 inch wide 5/8 inch nap roller to even out mix and apply final finish. Care must be taken to roll out “heavy” accumulations of coating. Heavy Duty system will yield an average of 32 dry mils over existing membrane.

B. EXISTING MEMBRANE SURFACES:

1. Complete all preparatory work before application begins. Apply intermediate and top coats with properly sized equipment to arrive at required mil thickness. Verify mil thickness of all coats by use of wet-mil thickness gauge.
2. Vacuum thoroughly all surfaces to be coated. Apply primer to all deck surfaces at manufacturers recommended application rate. Force primer into pores and voids to eliminate pinholes. Do not apply Primer over pre-striping.
3. Installation: **NEOGARD AUTO-GARD FC**
 - a. **Primer:** Apply 7795/7796 primer at a rate of 300-500 sf/gallon to all exposed concrete and coated surfaces in strict accordance with procedures outlined by NEOGARD®. **Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, re-prime.**
 - b. **Wearing Surface Coat for Medium Duty Applications:** Apply FC7510/7961 coat at a rate of 133 sf/gallon (12 mils) in strict accordance with procedures outlined by NEOGARD® and immediately broadcast **7992T aggregate**, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet.
 - d. **Additional Wearing Surface Coat for Heavy Duty (Turn Areas) Applications:** At all turn areas apply double-texture as follows: After the wearing surface coat to receive aggregate has cured and loose aggregate removed, apply FC510/7961 at a rate of 100 sf/gallon (16 mils) strict accordance with procedures outlined by NEOGARD® and immediately

broadcast additional **7992T aggregate**, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet.

- e. **Finish Top Coat:** When dry, remove excess aggregate and recoat surface with FC7510/7961 at rate of 100 sf/gallon (16 mils) in strict accordance with procedures outlined by NEOGARD®.
- f. Total system coating thickness averages 28 dry mils exclusive of aggregate. Double-textured areas will yield an average of 44 dry mils exclusive of aggregate.

4. Installation: **NEOGARD AUTO-GARD EAS**

- a. **Primer:** Apply 7795/7796 primer at a rate of 300-500 sf/gallon to all exposed concrete and coated surfaces in strict accordance with procedures outlined by NEOGARD®. **Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, re-prime.**
- b. **Wearing Surface Coat for Medium Duty Applications:** Mix elastomeric topcoat material FC7510/7961 for 3 to 5 minutes. Once mixed, add aggregate **7992T aggregate** at the rate of 10lbs/gallon and mix until thoroughly blended. Immediately place coatings/aggregate mix and spread with ¼” notched squeegee. Note: Depending on amount of time between mixing aggregate and placement of coating/aggregate mix, it may be necessary to agitate mix to suspend aggregate before placing. Apply coating/aggregate mix at a rate of 1.25 gallons per 100 square feet (80sf/gal) to yield an average of 20 dry mils. Use 18 inch wide 5/8 inch nap roller to even out mix and apply final finish. Care must be taken to roll out “heavy” accumulations of coating. Medium Duty system will yield an average of 20 dry mils over existing membrane.
- c. **Wearing Surface Coat for Heavy Duty (Turn Areas) Applications:** Mix elastomeric topcoat material FC7510/7961 for 3 to 5 minutes. Once mixed, add aggregate **7992T aggregate** at the rate of 10 lbs/gallon and mix until thoroughly blended. Immediately place coatings/aggregate mix and spread with ¼” notched squeegee. Note: Depending on amount of time between mixing aggregate and placement of coating/aggregate mix, it may be necessary to agitate mix to suspend aggregate before placing. Apply coating/aggregate mix at a rate of 2 gallons per 100 square feet (50sf/gal) to yield an average of 32 dry mils. Use 18 inch wide 5/8 inch nap roller to even out mix and apply final finish. Care must be taken to

roll out “heavy” accumulations of coating. Heavy Duty system will yield an average of 32 dry mils over existing membrane.

3.05 PROTECTION

- A. After completion of application, do not allow traffic on coated surfaces for a period of at least 24 - 36 hours at 75°F. and 50% R.H., or until completely cured.

3.05 FIELD QUALITY CONTROL

- A. Manufacturer's Field Service, Final inspection, and Warranty request: Manufacturer's representative will inspect finished surface preparation, application, and finished coating and may require further preparation or application to achieve appropriate result. In no case will manufacturer's representative approve surface or finish if following conditions are found: pinholes, insufficient coating thickness, or any other conditions, that, in manufacturer's representative's opinion, may cause failure of installation.

3.06 CLEANING

- A. Conform with specification Section 01710.
- B. Clean all equipment, tools, and spillage with manufacturer's recommend solvent.
- C. Clean up and properly dispose of all debris remaining on job site related to application.

END OF SECTION

SECTION 07920

JOINT SEALANTS

PART 1 – GENERAL

1.01 RELATED DOCUMENTS

1. The drawings and general conditions of the contract including General and Supplementary Conditions and other Division 1 Specification sections apply to work of this section.
2. Examine all other sections of the Specifications for requirements which affect work of this Section whether or not such work is specifically mentioned in this Section.
3. Coordinate work with that of all trades affecting or affected by work of this Section. Cooperate with such trades to assure the steady progress of all work under the Contract

1.02 DESCRIPTION OF WORK

- A. This Section includes joint sealants for the following locations:
 1. All joints in Cast-In-Place Concrete Toppings.

1.03 RELATED SECTIONS

- A. Concrete Repair: Section 03310.
- B. Traffic Membrane: Section 07180.

1.04 SYSTEM PERFORMANCE REQUIREMENTS

- A. Provide elastomeric joint sealants that have been produced and installed to establish and to maintain watertight and airtight continuous seals without causing staining or deterioration of joint substrates.

1.05 SUBMITTALS

- A. Unless otherwise specified, submittals required in this section shall be submitted for review. Submittals shall be prepared and submitted in accordance with 01300.
- B. All submittals shall be reviewed and returned within 10 working days.
- C. **Incomplete submittals will not be reviewed.**
- D. Submittals not reviewed by the General Contractor prior to submission to the Engineer will not be reviewed. Include on the submittal statement or stamp of approval by Contractor, representing that the Contractor has seen and examined the submittal and that all requirements listed in this Section and Division 1 have been complied with.
- E. Engineer will review submittals a maximum of two review cycles as part of their normal services. **If submittals are incomplete or otherwise unacceptable and re-submitted, General Contractor shall compensate the Owner for additional review cycles.**
- F. Product Data: Submit producer's or manufacturer's specifications and installation instructions for the following products. Include laboratory test reports and other data to show compliance with specifications (including specified standards).
 - 1. Joint Sealant Material.
 - 2. Certification that joint sealant product plus the primers and cleaners required for sealant installation comply with local regulations controlling use of volatile organic compounds.
 - 3. Warranty.

1.06 QUALITY ASSURANCE

- A. Codes and Standards: Comply with provisions of the following, except as otherwise indicated:
 - 1. ACI 504R-90 "Guide to Sealing Joints in Concrete Structures."
 - 2. SWR "Applying Liquid Sealants."
 - 3. SWR "Sealants: The Professionals Guide."
 - 4. "Code of Federal Regulations, Part 1926" per the Occupational Safety and Health Administration (OSHA), Department of Labor (Latest Revision).

- B. Installer Qualifications: Engage an experienced Installer who has completed joint sealant applications similar in material, design, and extent to that indicated for Project that have resulted in construction with a record of successful in-service performance.

1.07 DELIVERY, STORAGE, AND HANDLING

- A. Deliver Materials to Project site in original unopened containers or bundles with labels indicating manufacturer, product name and designation, color, expiration period for use, pot life, curing time, and mixing instructions for multicomponent materials.
- B. Store and handle materials in compliance with manufacturer's recommendations to prevent their deterioration or damage due to moisture, high or low temperatures, contaminants, or other causes.

1.08 PROJECT CONDITIONS

- A. Environmental Conditions: Do not proceed with installation of joint sealants under the following conditions:
 - 1. When ambient and substrate temperature conditions are outside the limits permitted by joint sealant manufacturer or below 40 deg. F.
 - 2. When joint substrates are wet.
- B. Joint Width Conditions: Do not proceed with installation of joint sealants where joint widths are less than or greater than that allowed by joint sealant manufacturer for application indicated.
- C. Joint Substrate Conditions: Do not proceed with installation of joint sealants until contaminants capable of interfering with their adhesion are removed from joint substrates.

1.09 WARRANTY

- A. System Manufacturer: Furnish Owner with written total responsibility guarantee that system will be free of defects, water penetration and chemical damage related to system design, workmanship or material deficiency, consisting of:
 - 1. Any adhesive or cohesive failures.
 - 2. Weathering
 - 3. Surface crazing.

- B. If material surface shows any of defects listed above, supply labor material to repair all defective areas and to repaint all damaged line stripes.
- C. Guarantee period shall be 5 yrs commencing with date of acceptable Work.
- D. Perform any repair under this guarantee at no cost to Owner.
- E. Before Construction, provide Owner with sample of final guarantee. Guarantee shall be provided by manufacturer.
- F. Vandalism and abnormally abrasive maintenance equipment are exempted from warranty.

PART 2- PRODUCTS

2.01 MATERIALS GENERAL

- A. Compatibility: Provide joint sealants, joint fillers, and other related materials that are compatible with one another, with joint substrates under conditions of service and application, as demonstrated by sealant manufacturer based on testing and field experience and the traffic membrane.

2.02 ELASTOMERIC JOINT SEALANTS

- A. General building sealants: 2 or 3-component, Type II, non-sag, urethane sealant, conforming to ASTM C 920.
- B. Accepted general building sealants:
 - 1. "Sonoplastic NP-2," Sonneborn, DeGussa Construction Chemicals.
 - 2. "Sikaflex-2C NS/TG," Sika Corp., Lyndhurst, NJ.
 - 3. Approved equal.
 - 4. Self-leveling products are not acceptable.
 - 5. All products must be traffic grade.
- C. Packing and backer rod: See heading, "Joint Sealant Backing."
- D. Sealants used shall not stain masonry or concrete. Aluminum pigmented compounds not acceptable.

2.03 MISCELLANEOUS MATERIALS

- A. Masking Tape: Nonstaining, nonabsorbent material compatible with joint sealants and surfaces adjacent to joints.

PART 3 – EXECUTION

3.01 EXAMINATION

- A. Examine joints indicated to receive joint sealants, with Installer present, for compliance with requirements for joint configuration, installation tolerances, and other conditions affecting joint sealant performance. Do not proceed with installation of joint sealants until unsatisfactory have been corrected.

3.02 PREPARATION

- A. Surface Cleaning of Joints: Clean out joints immediately before installing joint sealants to comply with recommendations of joint sealant manufacturer and the following requirements:
 1. Remove all foreign material from joint substrates that could interfere with adhesion of joint sealant, including dust, paints (except for permanent, protective coatings tested and approved for sealant adhesion and compatibility by sealant manufacturer), old joint sealants, oil, grease, waterproofing, water repellents, water, surface dirt, and frost.
 2. Clean concrete, masonry, and similar porous joint substrate surfaces by brushing, grinding, blast cleaning, mechanical abrading, or a combination of these methods to produce a clean, sound substrate capable of developing optimum bond with joint sealants. Remove loose particles remaining from above cleaning operations by vacuuming or blowing out joints with oil-free compressor.
 3. Remove laitance and form release agents from concrete.
- B. Joint Priming: Priming not required.
- C. Masking Tape: Use masking tape where required to prevent contact of sealant with adjoining surfaces that otherwise would be permanently stained or damaged by such contact or by cleaning methods required to remove sealant smears. Remove tape immediately after tooling without disturbing joint seal.

3.03 INSTALLATION OF JOINT SEALANTS

- A. General: Comply with joint sealant manufacturer's printed installation instructions applicable to products and applications indicated, except where more stringent requirements apply.
- B. Sealant Installation Standard: Comply with recommendations of ASTM C 1193 for use of joint sealants as applicable to materials, applications, and conditions indicated.
- C. Installation of Sealants: Install sealants by proven techniques that result in sealants directly contacting and fully wetting joint substrates, completely filling recesses provided for each joint configuration, and providing uniform, cross-sectional shapes and depths relative to joint widths that allow optimum sealant movement capability. Install sealants at the same time sealant backings are installed.
- D. Tooling of Non sag Sealants: Immediately after sealant application and prior to time skinning or curing begins, tool sealants to form smooth, uniform beads of configuration indicated, to eliminate air pockets, and to ensure contact and adhesion of sealant with sides of joint. Remove excess sealants from surfaces adjacent to joint. Do not use tooling agents that discolor sealants or adjacent surfaces or are not approved by sealant manufacturer.
 - 1. Provide concave joint configuration per Figure 5A in ASTM C 1193, unless otherwise indicated.
 - a. Use masking tape to protect adjacent surfaces of recessed tooled joints.

3.04 CLEANING

- A. Clean off excess sealants or sealant smears adjacent to joints as work progresses by methods and with cleaning materials approved by manufacturers of joint sealants and of products in which joints occur.

3.05 PROTECTION

- A. Protect joint sealants during and after curing period from contact with contaminating substances or from damage resulting from construction operations or other causes so that they are without deterioration or damage at time of Substantial Completion. If, despite such protection, damage or deterioration occurs, cut out and remove damaged or deteriorated joint sealants immediately so that and installations with repaired areas are indistinguishable from original work.

END OF SECTION

DIVISION 9

FINISHES

SECTION 09900

PAINTING

PART 1 GENERAL

1.00 GENERAL PROVISIONS:

- A. The CONDITIONS OF THE CONTRACT and all Sections of Division 1 are hereby made a part of this Section.

1.01 DESCRIPTION OF WORK:

- B. Removal of existing deterioration, prepare surface, and re-paint structural steel as indicated in the contract documents.
- C. Related Work: Examine Contract Documents for requirements that affect work of this Section. Other Specification Sections that directly relate to work of this Section include but are not limited to:
 - 1. Selective Demolition: SECTION 02070.
 - 2. Structural Steel: SECTION 05210

1.02 QUALITY ASSURANCE:

- D. Applicator Qualifications: Engage an experienced applicator who has a minimum of successful years experience with high performance coating systems and their application in renovation.
- B. Source Limitations: Obtain primers and undercoat materials for each coating system from the same manufacturer as the finish coats.
- C. Sample: Provide a full coat benchmark finish sample on existing steel member for color approval.
 - 1. Color to match existing.
 - 2. Final approval of colors will be from sample.
- D. Standards: Comply with applicable recommendations made by following:
 - 1. SSPC Painting Manual – eighth edition.

1.03 SUBMITTALS:

- A. General: Comply with requirements of SECTION 01300-SUBMITTALS.

B. Product Data:

1. Submit manufacturer's printed product data, specifications, use limitations and recommendations for each material used. Provide certifications that the materials and systems comply with specified requirements.

C. Certification by manufacturer that product supplied comply with requirements indicated that limit the amount of VOC's in coating products.

D. Qualification Data:

1. Include list of completed projects with names and addresses of project, owner, and general contractor (if applicable).

1.04 TESTS:

- A. Owner may employ an independent testing agency to perform test, evaluations, and certifications of products used. Cooperate and permit samples of material to be taken as they are needed.

1.05 PRODUCT DELIVERY, STORAGE AND HANDLING:

- A. Deliver materials in manufacturer's original, unopened packages and containers bearing manufacturer's name and label.

- B. Store materials in fully sealed containers in a well ventilated area at a minimum ambient temperature of 45 deg F (7 deg C).

1. Remove oily rags and waste daily.

2. Protect materials from freezing.

3. Each space containing stored paint materials shall be provided with a UL labeled fire extinguisher of suitable type, class, and capacity.

1.06 JOB CONDITIONS, PROTECTION:

- A. Apply coatings only when temperature of surfaces to be coated and surrounding air temperatures are between 45 and 95 deg F (7 and 35 deg C). Unless otherwise indicated and warranted by manufacturer.

- B. Do not apply coatings in snow, rain, fog, or mist: when relative humidity exceeds 85 percent; at temperatures less than 5 deg F (3 deg C) above the dew point; or to damp or wet surfaces.

- C. Post wet paint signs immediately after application and maintain until paint has cured.

1.07 WARRANTY

- A. Provide 5 year written guarantee that re-painted areas will be free of defects related to workmanship, material, deficiency and exposure.

PART 2 PRODUCTS AND EXPOSURE

2.00 Provide sample warranty for review by owner prior to commencing work.

2.01 MANUFACTURERS

- A. Products: Subject to compliance with requirements, provide one of the products indicated in the coating system descriptions.
- B. Manufacturers' Names: The following manufacturers are referred to in the coating system descriptions by shortened versions of their names shown in parenthesis:
 - 1. ICI Dulux Paints; Deveo Coatings (ICI).
 - 2. Tnemec Company, Inc. (Tnemec).
 - 3. International Protective Coatings (IPC).
 - 4. Approved equal
- C. Obtain owner's approval prior to purchase and delivery.

2.02 COATING MATERIALS, GENERAL:

- A. Assume full responsibility for proper performance of materials, for method of application, and for compatibility of materials applied over other coats previously applied, including but not limited to primers, sealers, preservative treatments, etc. Select primers which have been verified to be appropriate for each of the substrates and finishes encountered.
- B. Material Quality: Provide manufacturer's highest grade of the various high-performance coatings specified. Materials not displaying manufacturer's product identification are not acceptable.
- C. VOC Classification: Provide high-performance coating materials, including primers, undercoats and finish coats that have a VOC classification of 450 g/L or less.

2.03 COLOR:

- A. Color: Match existing.

PART 3 EXECUTION

3.00 EXAMINATION:

- A. Inspect all surfaces to receive finishes to ensure they are in proper condition to receive work under this Section.
 - 1. Apply coatings only after unsatisfactory conditions have been corrected and surfaces to receive coatings are thoroughly dry.
 - 2. Start of application is construed as acceptance of the surface as being satisfactory to the Applicator.

3.01 PREPARATION:

- A. Prepare surfaces to receive work of this Section in strict accordance with the manufacturer's instructions applicable to each material, condition and finish.
- B. Existing Ferrous Metal:
 - 1. SSPC-SP6/NACE 3 Commercial Blast Cleaning: Removal of all visible oil, grease, dust, dirt, mill scale, rust, paint oxides, corrosion products and other foreign matter by compressed air nozzle blasting, centrifugal wheels or other specified method.
 - 2. Remove all dust and blast products from surface by high pressure air, vacuum cleaning or brushing.

3.02 APPLICATION:

- A. Apply high-performance paints in strict accordance with manufacturer's instructions. Use applicators and techniques best suited for substrates and types of materials being applied. No material shall be thinned in any way except as directed by manufacturer.
- B. Apply high performance paints at coverage rates and dry film thickness (DFT) as indicated:
 - 1. Primer: Epoxy primer applied at spreading rate recommended by manufacturer.
 - a. 2-3 mils DFT.
 - 2. Stripe/Brush Coat: Epoxy intermediate coat applied to all steel edges.
 - a. 4-6 mils DFT
 - 3. Intermediate Coat: Epoxy intermediate coat applied at spreading rate recommended by manufacturer.
 - a. 4-6 mils DFT
 - 4. Top Coat: Semigloss top coat applied at spreading rate recommended by manufacturer
 - a. 4-6 mils DFT

- C. Drying Time: Allow manufacturer's recommended drying time between successive coats. Ensure each coat has thoroughly dried prior to application of subsequent coat.

3.03 COMPLETION:

- A. Cleaning: At completion of work of this Section, remove paint, oil, grease, and other stains caused by this work from the exposed surfaces. Leave finishes in satisfactory condition.
- B. At completion of work of this Section, remove masking materials and other debris. Reinstall or replace fixtures, plates etc., removed to facilitate application of paint.

END OF SECTION