



CALIFORNIA DEPARTMENT OF FORESTRY and FIRE PROTECTION
OFFICE OF THE STATE FIRE MARSHAL

REGISTERED FLAME RESISTANT PRODUCT

Product:

COOLEY BRITE

Registration No.


F-10207

Product Marketed By:

COOLEY
50 ESTEN AVE
PAWTUCKET, RI 02860

This product meets the minimum requirements of flame resistance established by the California State Fire Marshal for products identified in Section 13115, California Health and Safety Code.

The scope of the approved use of this product is provided in the current edition of the **CALIFORNIA APPROVED LIST OF FLAME RETARDANT CHEMICALS AND FABRICS, GENERAL AND LIMITED APPLICATIONS CONCERNS** published by the California State Fire Marshal.


Deputy State Fire Marshal

Expire: 6/30/2015

MAGILL LABORATORIES, INC.

P.O. Box 267 • One Railroad Street
Slatersville, Rhode Island 02876

tel (401) 766-7972 Fax (401) 766-7974
www.magilllaboratories.com

LABORATORY REPORT

QLL 18030

TEST REPORT #415

DATE: 03 MAY 2004

THE COOLEY GROUP
P.O. BOX 939
PAWTUCKET, RI 02862

ATTENTION: ROBERT VENICE

P.O. #27228

SUBJECT: ONE (1) SAMPLE OF COATED FABRIC TESTED FOR FLAME RESISTANCE
IN ACCORDANCE WITH NFPA 701-99, TEST METHOD 2, INITIAL AND
AFTER LEACHING.

IDENTIFIED AS: COOLEY BRITE

TESTING COMPLETED: 03 MAY 2004

<u>TEST, UNIT OF MEASURE</u>	<u>RESULTS</u>	<u>REQUIREMENTS</u>
Flame Resistance TEST 2 (NFPA 701-1999 CHAPTER 12)		
INITIAL		
AFTER FLAME, SECONDS		
MACHINE DIRECTION	0.0	
	0.0	
	0.0	
	0.0	
	0.0	
	0.0	
	0.0	
	0.0	
	0.0	
Average:	0.0	2.0 MAXIMUM
CHAR LENGTH, INCHES	7.2	
	6.7	
	6.9	
	8.9	
	8.1	
	7.6	
	6.0	
	8.1	
	7.3	
	7.1	

Average: 7.4

17.1 MAXIMUM

This report is for the exclusive use of the client to whom it is addressed and its communication to any others or use of the name Magill Laboratories must receive our prior written approval. This report is applicable only to the sample or samples tested.

