

SECTION 04065

MASONRY MORTAR AND GROUT

1 PART 1 GENERAL

1.1 RELATED DOCUMENTS

- A. Drawings and general provisions of Contract including General and Supplementary Conditions and Division 1 specification sections, apply to work of this section.

1.2 SECTION INCLUDES

- A. Mortar and grout for masonry.

1.3 SUBMITTALS

- A. Samples: Submit two samples of mortar, illustrating mortar color and color range.

1.4 QUALITY ASSURANCE

- A. Perform Work in accordance with ACI 530 and ACI 530.1, and TMS MSJC Code and Specifications.

1.5 ENVIRONMENTAL REQUIREMENTS

- A. Hot and Cold Weather Requirements: Comply with ACI 530.1/TMS 602.

2 PART 2 PRODUCTS

2.1 MATERIALS

- A. Portland Cement: ASTM C150, Type I gray color, low alkali content.
- B. Mortar Aggregate: ASTM C144, standard masonry type, washed sand.
- B. Hydrated Lime: ASTM C207, Type S.
- C. Mortar Color: Mineral oxide pigment color as follows:
 - 1. At Red Brick: SGS 25H Deep Tan
 - 2. At Light Buff Brick: SGS 10H Light Buff.
 - 3. At Dark Buff Brick: SGS 20H Dark Buff.
- D. Grout Aggregate: ASTM C404.
- E. Water: Clean and potable, salt free.
- F. Bonding Agent: Epoxy type.
- G. Prism Strength: Type S Mortar – 1,800 psi.

2.2 MORTAR MIXES

- A. Mortar for Load Bearing Walls and Partitions: ASTM C270, Type M using the Property Method.
- B. Mortar for Brick Veneer Walls: ASTM C270, Type S using the Property Method.
- C. Mortar for Reinforced Masonry: ASTM C270, Type S using the Property Method.

2.3 MORTAR MIXING

- A. Thoroughly mix mortar ingredients in quantities needed for immediate use in accordance with ASTM C270.
- B. Add mortar color in accordance with manufacturer's instructions.
- C. Do not use anti-freeze compounds to lower the freezing point of mortar. The use of calcium chloride is strictly prohibited.
- D. Mortar preparation shall be per admixture manufacturer's standard recommendations.

2.4 GROUT MIXES

- A. Bond Beams, Engineered Masonry: 3,000 psi strength at 28 days; 8-10 inches slump; premixed type in accordance with ASTM C94 .

2.5 GROUT MIXING

- A. Mix grout in accordance with ASTM C94.
- B. Do not use anti-freeze compounds to lower the freezing point of grout.

2.6 MIX TESTS

- A. Testing of Mortar Mix: In accordance with ASTM C780.
- B. Testing of Grout Mix: In accordance with ASTM C1019.

3 PART 3 EXECUTION

3.1 INSTALLATION

- A. Install mortar in accordance with TMS MSJC Specifications.
- B. Work grout into masonry cores and cavities to eliminate voids. Do not displace reinforcement.

3.2 SCHEDULES

- A. Exterior Face Brick Wall: Type S mortar, in colors as scheduled.

...END OF SECTION 04065