


DIVERSIFIED
TESTING LABORATORIES, INC.



336 WEST FRONT STREET
PO BOX 4004
BURLINGTON, NORTH CAROLINA 27215
Phone (336) 227-7710 • Fax (336) 227-1175

"We Test Per Your Request!"

January 9, 2003

Mrs. Catherine MERILLION
FERRARI SA
BP 54
38352 La Tour Du Pin Cedex
La Mure, France

Reference: Laboratory Test Report
Lab Identification No. 5349
Invoice No. A270 (Attached)

Dear Ms. MERILLION:

One (1) fabric sample, identified as PRECONTRADIF 702, was received and tested in accordance with the National Fire Prevention Association No. 701, "Flame Propagation of Textiles and Films, 1999 Edition. (Test 2, Large Scale)." The results are as follows:

Specimen Number	Afterflame (seconds)	Residual Flame (seconds)	Char Length (inches)
Single 1	0.0	0.0	10.0
Flat 2	0.0	0.0	11.0
Specimen 3	0.0	0.0	11.0
4	0.0	0.0	10.0
5	0.0	0.0	10.0
6	0.0	0.0	10.0
7	0.0	0.0	12.0
8	0.0	0.0	7.0
9	0.0	0.0	10.0
10	0.0	0.0	8.0

The sample submitted meets the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no remainder shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karen Watkins
Karen S. Watkins

CJK/mr
Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY LOGO MUST PEGIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITY OF ANYBODY'S MATERIAL OR PROPERTY. SAMPLES NOT SUBMITTED IN TESTING ARE RETAINING A MAXIMUM OF THIRTY DAYS. THE LETTERS REPORTED ON NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.