

Report of Concrete Compressive Strength

ASTM C-31 & C-39

Project Name: PORTLAND - FORE RIVER SHORT STAY HOSPITAL
 PROJECT - MATERIALS TESTING / SPECIAL

Project Number: 06-1069.1

Client: MERCY HOSPITAL

Client Contract Number:
General Contractor:
Concrete Supplier: DRAGON PRODUCTS

PLACEMENT INFORMATION

Date Cast: 4/20/2007 **Time Cast:** 4:15 **Date Received:** 4/21/2007

Placement Location: 2ND FLOOR LEFT HALF

Placement Method: PUMP TRUCK

Placement Vol. (yd³): 265

Cylinders Made By: JCM

Aggregate Size (in): 3/4

INITIAL CURING CONDITIONS

Temperatures

Minimum (°F) **Maximum (°F)**

DELIVERY INFORMATION

Admixtures: POLYHEED 997 /
 POZZUTEC 20 1%

TEST RESULTS

Slump (in) (C-143): 4.75

Load Number: 10

Air Content (%) (C-231): 1.6

Mixer Number: 140

Air Temp (°F): 46

Ticket Number: 4525971

Conc. Temp (°F) (C-1064): 53

Cubic Yards: 10

Design (psi): 4000

Cylinder Designation	Cylinder Weight (lbs)	Cylinder Diameter (in)	Cross Sectional Area(In) ²	Date Of Test	Cure Type	Age (days)	Fracture Type	Load (kips)	Strength (psi)
702-56A		6.00	28.27	4/27/2007	Lab	7	4	109.0	3860
702-56B		6.00	28.27	5/18/2007	Lab	28	4	146.5	5180
702-56C		6.00	28.27	5/18/2007	Lab	28	4	145.5	5150
702-56D				Hold	Lab				

Fracture Types



Cone



Cone and Split



Cone and Shear



Shear



Columnar

Remarks: