



CALIFORNIA DEPARTMENT OF FORESTRY and FIRE PROTECTION
OFFICE OF THE STATE FIRE MARSHAL

REGISTERED FLAME RESISTANT PRODUCT

Product:
WEATHERTYTE LITE

Registration No.
F-75301

Product marketed By:
COOLEY, INC.
50 ESTEN AVENUE
PAWTUCKET, RI 02860

This product meets the minimum requirements of flame resistance established by the California State Fire Marshal for products identified in Section 13115, California Health and Safety Code.

The scope of the approved use of this product is provided in the current edition of the **CALIFORNIA APPROVED LIST OF FLAME RETARDANT CHEMICALS AND FABRICS, GENERAL AND LIMITED APPLICATIONS CONCERNS** published by the California State Fire Marshal.

Deputy State Fire Marshal

Expire: 6/30/2011



MAGILL LABORATORIES, INC.

458 Wild Ammonoosuc Road
Bath, New Hampshire 03740

Tel (603) 747-4111 Fax (603) 747-4112
www.magilllaboratories.com

LABORATORY REPORT

QLL 18030

DATE: 30 SEPTEMBER 2008

TEST REPORT #080893

THE COOLEY GROUP
P.O. BOX 939
PAWTUCKET, RI 02862

ATTENTION: **MICHAEL DESOUTO**

SUBJECT: ONE (1) SAMPLE OF FABRIC TESTED FOR **FLAME RESISTANCE** IN
ACCORDANCE WITH **NFPA 701-2004, TEST METHOD 2.**

IDENTIFIED AS: **WEATHERTYTE LITE**

TESTING COMPLETED: 30 SEPTEMBER 2008

<u>TEST, UNIT OF MEASURE</u>	<u>RESULTS</u>	<u>REQUIREMENTS</u>
Flame Resistance (NFPA 701 – 2004)		
TEST METHOD 2 - FOLD		
AFTERFLAME, SECONDS	0.0 0.0 0.0 0.0	
Average:	0.0	2.0 MAXIMUM
CHAR LENGTH, INCHES	19.6 17.3 20.0 20.1	
Average:	19.3	41.3 MAXIMUM

This report is for the exclusive use of the client to whom it is addressed and its communication to any others or use of the name Magill Laboratories must receive our prior written approval. This report is applicable only to the sample or samples tested.



MAGILL LABORATORIES, INC.
TEST REPORT #080893

PAGE -2-

30 SEPTEMBER 2008

<u>TEST, UNIT OF MEASURE</u>	<u>RESULTS</u>	<u>REQUIREMENTS</u>
------------------------------	----------------	---------------------

Flame Resistance
(NFPA 701 – 2004)

TEST METHOD 2 - FOLD

DRIPPING AND FLAMING, SECONDS

0.0
0.0
0.0
0.0

Average:	0.0	2.0 MAXIMUM
----------	-----	-------------

THE SAMPLE TESTED ABOVE **MEETS** THE REQUIREMENTS OUTLINED
IN CHAPTER 15 OF NFPA 701-2004, TEST METHOD 2.

I certify that the above tests were performed under my supervision in accordance with the specification test requirements and that the reported test results are true, valid and applicable to the samples tested. I further certify that these samples are the only samples tested from the lot of components identified above.

Signed 
Edward L. Magill Jr.
President