


# Report of Moisture-Density

Method ASTM D-1557 MODIFIED Procedure A

Project Name PORTLAND ME - THE PARK DANFORTH - CONSTRUCTION  
MATERIALS TESTING SERVICES  
Client THE PARK-DANFORTH  
Material Type GRANULAR BORROW  
Material Source NATIVE MATERIAL

Project Number 14-0065.2  
Lab ID 20399G  
Date Received 1/7/2016  
Date Completed 1/8/2016  
Tested By PAUL SHAFFER

## Moisture-Density Relationship Curve



Maximum Dry Density (pcf) 116.3  
Optimum Moisture Content (%) 10.5  
Percent Oversized 19.1%

Corrected Dry Density (pcf) **122.4**  
Corrected Moisture Content (%) **8.9**

Comments

Roger E. Domingo