

Report of Concrete Compressive Strength

ASTM C-31 & C-39

Project Name: PORTLAND - THE INN AT CEDARS - MATERIALS TESTING

Project Number: 07-0503

Client: THE OSHER INN AT CEDARS

Client Contract Number:

General Contractor:

Concrete Supplier: AUBURN CONCRETE

PLACEMENT INFORMATION

Date Cast: 10/26/2007 **Time Cast:** 8:00 **Date Received:** 10/27/2007

Placement Location: FIRST FLOOR SLAB

Placement Method: PUMP

Placement Vol. (yd³): 200

Cylinders Made By: CKT

Aggregate Size (in): 3/4

INITIAL CURING CONDITIONS

Temperatures

Minimum (°F) **Maximum (°F)**

DELIVERY INFORMATION

Admixtures:

TEST RESULTS

Slump (in) (C-143): 6 1/4

Load Number: 4

Air Content (%) (C-231): 2.3

Mixer Number: 116

Air Temp (°F): 45

Ticket Number: 135251

Conc. Temp (°F) (C-1064): 56

Cubic Yards: 10

Design (psi): 3000

Cylinder Designation	Cylinder Weight (lbs)	Cylinder Diameter (in)	Cross Sectional Area(In) ²	Date Of Test	Cure Type	Age (days)	Fracture Type	Load (kips)	Strength (psi)
774-9A		6.00	28.27	11/2/2007	Lab	7	4	89.5	3170
774-9B				11/23/2007	Lab	28			
774-9C				11/23/2007	Lab	28			
774-9D				Hold	Lab				

Fracture Types



Cone




Cone and Split



Cone and Shear



Shear



Columnar

Remarks:

Project Name: PORTLAND - THE INN AT CEDARS - MATERIALS TESTING

Project Number: 07-0503

Client: THE OSHER INN AT CEDARS

Client Contract Number:

General Contractor:

Concrete Supplier: AUBURN CONCRETE

PLACEMENT INFORMATION

Date Cast: 10/26/2007 **Time Cast:** 8:30 **Date Received:** 10/27/2007

Placement Location: FIRST FLOOR SLAB

Placement Method: PUMP

Placement Vol. (yd³): 200

Cylinders Made By: CKT

Aggregate Size (in): 3/4

INITIAL CURING CONDITIONS

Temperatures

Minimum (°F) **Maximum (°F)**

DELIVERY INFORMATION

Admixtures:

TEST RESULTS

Slump (in) (C-143): 5.5

Load Number: 6

Air Content (%) (C-231): 2.1

Mixer Number: 98

Air Temp (°F): 46

Ticket Number: 135256

Conc. Temp (°F) (C-1064): 56

Cubic Yards: 10

Design (psi): 3000

Cylinder Designation	Cylinder Weight (lbs)	Cylinder Diameter (in)	Cross Sectional Area(In) ²	Date Of Test	Cure Type	Age (days)	Fracture Type	Load (kips)	Strength (psi)
774-10A		6.00	28.27	11/2/2007	Lab	7	4	94.0	3330
774-10B				11/23/2007	Lab	28			
774-10C				11/23/2007	Lab	28			
774-10D				Hold	Lab				

Fracture Types



Cone



Cone and Split



Cone and Shear



Shear



Columnar

Remarks:

Report of Concrete Compressive Strength

ASTM C-31 & C-39

Project Name: PORTLAND - THE INN AT CEDARS - MATERIALS TESTING

Project Number: 07-0503

Client: THE OSHER INN AT CEDARS

Client Contract Number:
General Contractor:
Concrete Supplier: AUBURN CONCRETE

PLACEMENT INFORMATION

Date Cast: 10/26/2007 **Time Cast:** 9:10 **Date Received:** 10/27/2007

Placement Location: FIRST FLOOR SLAB

Placement Method: PUMP

Placement Vol. (yd³): 200

Cylinders Made By: CKT

Aggregate Size (in): 3/4

INITIAL CURING CONDITIONS

Temperatures

Minimum (°F) **Maximum (°F)**

DELIVERY INFORMATION

Admixtures:

TEST RESULTS

Slump (in) (C-143): 4 3/4

Load Number: 10

Air Content (%) (C-231): 2.1

Mixer Number: 97

Air Temp (°F): 48

Ticket Number: 135262

Conc. Temp (°F) (C-1064): 56

Cubic Yards: 10

Design (psi): 3000

Cylinder Designation	Cylinder Weight (lbs)	Cylinder Diameter (in)	Cross Sectional Area(In) ²	Date Of Test	Cure Type	Age (days)	Fracture Type	Load (kips)	Strength (psi)
774-11A		6.00	28.27	11/2/2007	Lab	7	4	102.5	3630
774-11B				11/23/2007	Lab	28			
774-11C				11/23/2007	Lab	28			
774-11D				Hold	Lab				

Fracture Types



Cone



Cone and Split



Cone and Shear



Shear



Columnar

Remarks:

Report of Concrete Compressive Strength

ASTM C-31 & C-39

Project Name: PORTLAND - THE INN AT CEDARS - MATERIALS TESTING

Project Number: 07-0503

Client: THE OSHER INN AT CEDARS

Client Contract Number:
General Contractor:
Concrete Supplier: AUBURN CONCRETE

PLACEMENT INFORMATION

Date Cast: 10/26/2007 **Time Cast:** 10:20 **Date Received:** 10/27/2007

Placement Location: FIRST FLOOR SLAB

Placement Method: PUMP

Placement Vol. (yd³): 200

Cylinders Made By: CKT

Aggregate Size (in): 3/4

INITIAL CURING CONDITIONS

Temperatures

Minimum (°F) **Maximum (°F)**

DELIVERY INFORMATION

Admixtures:

TEST RESULTS

Slump (in) (C-143): 5

Load Number: 13

Air Content (%) (C-231): 2.8

Mixer Number: 116

Air Temp (°F): 48

Ticket Number: 135267

Conc. Temp (°F) (C-1064): 56

Cubic Yards: 10

Design (psi): 3000

Cylinder Designation	Cylinder Weight (lbs)	Cylinder Diameter (in)	Cross Sectional Area(In) ²	Date Of Test	Cure Type	Age (days)	Fracture Type	Load (kips)	Strength (psi)
774-12A		6.00	28.27	11/2/2007	Lab	7	4	92.0	3250
774-12B				11/23/2007	Lab	28			
774-12C				11/23/2007	Lab	28			
774-12D				Hold	Lab				

Fracture Types



Cone




Cone and Split



Cone and Shear



Shear



Columnar

Remarks:

Report of Concrete Compressive Strength

ASTM C-31 & C-39

Project Name: PORTLAND - THE INN AT CEDARS - MATERIALS TESTING

Project Number: 07-0503

Client: THE OSHER INN AT CEDARS

Client Contract Number:
General Contractor:
Concrete Supplier: AUBURN CONCRETE

PLACEMENT INFORMATION

Date Cast: 10/26/2007 **Time Cast:** 11:50 **Date Received:** 10/27/2007

Placement Location: FIRST FLOOR SLAB

Placement Method: PUMP

Placement Vol. (yd³): 200

Cylinders Made By: CKT

Aggregate Size (in): 3/4

INITIAL CURING CONDITIONS

Temperatures

Minimum (°F) **Maximum (°F)**

DELIVERY INFORMATION

Admixtures:

TEST RESULTS

Slump (in) (C-143): 5

Load Number: 18

Air Content (%) (C-231): 2.4

Mixer Number: 118

Air Temp (°F): 54

Ticket Number: 135276

Conc. Temp (°F) (C-1064): 58

Cubic Yards: 10

Design (psi): 3000

Cylinder Designation	Cylinder Weight (lbs)	Cylinder Diameter (in)	Cross Sectional Area(In) ²	Date Of Test	Cure Type	Age (days)	Fracture Type	Load (kips)	Strength (psi)
774-13A		6.00	28.27	11/2/2007	Lab	7	4	100.5	3560
774-13B				11/23/2007	Lab	28			
774-13C				11/23/2007	Lab	28			
774-13D				Hold	Lab				

Fracture Types



Cone




Cone and Split



Cone and Shear



Shear



Columnar

Remarks: