

R. W. Gillespie & Associates, Inc.

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008
200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244

LETTER OF TRANSMITTAL

Doughty & Associates, Inc.

362 U.S. Route One

Falmouth, ME 04105

Date:	July 1, 2004	Project No.:	438-05
Attention:	Mr. Phillip Doughty (pdarch@maine.rr.com)		
Re:	Concrete Testing New Jetways & Addition to Baggage Claim Portland Jetport Portland, Maine		

We are sending you attached concrete cylinder test results.

Cylinder No. (s)	Age (Days)
46590	28
46591	28

Remarks:

Copy To: Roy Williams (rsw@ci.portland.me.us)

Signed: Bertha Dawn

If enclosures are not as noted, kindly notify us at once.

R. W. GILLESPIE & ASSOCIATES, INC.

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008
 200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244
CONCRETE TEST/PLACEMENT REPORT

Project Name: New Jetways & Addition to Baggage Claim
Project No: 438-05
Weather Conditions: Cloudy / Rain
Method of Placement: Excavator & Bucket
Admixtures: --
Placement Location: Utility Manhole - Walls
Test Cylinder Location: Wall closest to the tower

Date Cylinders Cast: 03-Jun-04
Concrete Supplier: Auburn
General Contractor: Ledgewood
Design Strength: 4,000
Max Agg. Size: 3/4"

Date Report Issued: ~~Jul 02 2004~~

6x12 Cylinders	4	Cast by	Marco C. Stone			
Load No.	1	Slump (in) ASTM C 143	4.5	Time		
Ticket No.	061232	Air (°F)	60		Batched @	12:18
Truck No.	68	Concrete (°F) ASTM C 1064	78		Arrived @	12:32
Cubic Yds.	4.5	Air Content (%) ASTM C 231	6.4		Total Time	30

*Concrete sampled by ASTM C 172

Specimen Storage ASTM C 31: Field cure days: 1
 Date received: 04-Jun-04
 Condition of Cylinders: Good


Lab No.	Test Date	Avg Dia (in)	Area (in ²)	Age (Days)	Load (lbs)	Compressive Strength (psi)	Break type
46589	10-Jun-04	5.998	28.26	7	69,560	2460	4
46590	01-Jul-04	6.005	28.32	28	97,320	3440	4
46591	01-Jul-04	6.005	28.32	28	101,240	3575	4
46592	29-Jul-04			56			

*Concrete compressive strength by ASTM C 39

Types of Breaks



Cone
1



Cone & Split
2



Cone & Shear
3



Shear
4



Columnar
5

Load	Ticket Number	Truck Number	Cubic Yds	Slump (inches)	Air Temp (°F)	Conc Temp (°F)	(%) Air Content	Time (min.)
2	061240	68	3.50	--	--	--	--	47

Remarks:

Checked by:
 George S. Morrell, Supervisor