R. W. Gillespie & Associates, Inc.

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008 200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244

LETTER OF TRANSMITTAL

	Date:		Project No.:
		August 19, 2004	438-05
	Attention:		
		Mr. Phillip Dou	ighty (pdarch@maine.rr.com)
	Re:		
Doughty & Associates, Inc.		Concrete Testin	ıg
		New Jetways &	Addition to Baggage Claim
362 U.S. Route One		Portland Jetport	t
		Portland, Maine	•
Falmouth, ME 04105			

	We are sending y	ou attached concrete cylinder test results.	
Cylinder No. (s)		Age (Days)	
	47716	7	

Remarks:

Copy To: Roy Williams (rsw@ci.portland.me.us)

Signed:

Bertha Dawn

R. W. GILLESPIE & ASSOCIATES, INC.

Page 1 of 1

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008 200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244

CONCRETE TEST/PLACEMENT REPORT

Project Name:

New Jetways & Addition to Baggage Claim

Project No:

438-05 Overcast

Weather Conditions:
Method of Placement:

Pump

Admixtures:

Superplasticizer

Placement Location:

Piers: 47/X, 44/X, 41/X; Z/5' West of 47 - 40

Test Cylinder Location: X/47, X/44

Date Cylinders Cast:

11-Aug-04

Concrete Supplier:

Auburn

General Contractor: Design Strength:

Ledgewood

Max Agg. Size:

3,000 3/4

Date Report Issued:

6x12 Cylinders	4	Cast by Michae	el J. Kramlich	Time		
Load No.	1	Slump (in) ASTM C 143	8.0		Batched @	
Ticket No.	070515	Air (°F)	82		Arrived @	
Truck No.	97	Concrete (°F) ASTM C 1064	77		Total Time	50
Cubic Yds.	10.5	Air Content (%) ASTM C 231	4.5			

^{*}Concrete sampled by ASTM C 172

Specimen Storage ASTM C 31: Field cure days: 1

Date received: 12-Aug-04 Condition of Cylinders: Good

Lab No.	Test Date	Avg Dia (in)	Area (in²)	Age (Days)	Load (lbs)	Compressive Strength (psi)	Break type
47716	18-Aug-04	6.008	28.35	7	87,140	3070	4
47717	08-Sep-04			28			
47718	08-Sep-04			28			
47719	HOLD			HOLD			

^{*}Concrete compressive strength by ASTM C 39

Types of Breaks











Cone

Cone & Split Cone & Shear 3

Shear

Columnar 5

Load	Ticket	Truck	Cubic Yds	Slump	Air Temp	Conc Temp	(%) Air	Time
Number	Number		(inches)	(°F)	(°F)	Content	(min.)	
2	70517	88	10.50					50
3	70518	98	10.50					
4	70520	101	10.50					
·								

Remarks:

Checked by:

George S. Morrell, Supervisor