

R. W. Gillespie & Associates, Inc.

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008
200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244

LETTER OF TRANSMITTAL

Doughty & Associates, Inc.

362 U.S. Route One

Falmouth, ME 04105

Date:	September 13, 2004	Project No.:	438-05
Attention:	Mr. Phillip Doughty (pdarch@maine.rr.com)		
Re:	Concrete Testing New Jetways & Addition to Baggage Claim Portland Jetport Portland, Maine		

We are sending you attached concrete cylinder test results.

Cylinder No. (s)	Age (Days)
48339	7

Remarks:

Copy To: Roy Williams (rsw@ci.portland.me.us)

Signed: Bertha Dawn

If enclosures are not as noted, kindly notify us at once.

R. W. GILLESPIE & ASSOCIATES, INC.
 86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008
 200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244
CONCRETE TEST/PLACEMENT REPORT

Project Name:	New Jetways & Addition to Baggage Claim	Date Cylinders Cast:	03-Sep-04
Project No:	438-05	Concrete Supplier:	Auburn
Weather Conditions:	Sunny	General Contractor:	Ledgewood
Method of Placement:	Rear discharge	Design Strength:	3,000
Admixtures:	Superplasticizer	Max Agg. Size:	3/4
Placement Location:	E/18		
Test Cylinder Location:	E/18		

Date Report Issued: SEP 14 2004

6x12 Cylinders	4	Cast by	Michael J. Kramlich	Time	
Load No.	1	Slump (in) ASTM C 143	8	Batched @	--
Ticket No.	071125	Air (°F)	84	Arrived @	--
Truck No.	47	Concrete (°F) ASTM C 1064	80	Total Time	50
Cubic Yds.	10.75	Air Content (%) ASTM C 231	4.2		


*Concrete sampled by ASTM C 172

Specimen Storage ASTM C 31: Field cure days: 1
 Date received: 04-Sep-04
 Condition of Cylinders: Good

Lab No.	Test Date	Avg Dia (in)	Area (in ²)	Age (Days)	Load (lbs)	Compressive Strength (psi)	Break type
48339	10-Sep-04	6.005	28.32	7	92,220	3260	4
48340	01-Oct-04			28			
48341	01-Oct-04			28			
48342	HOLD			HOLD			

*Concrete compressive strength by ASTM C 39

Types of Breaks



Load	Ticket Number	Truck Number	Cubic Yds	Slump (inches)	Air Temp (°F)	Conc Temp (°F)	(%) Air Content	Time (min.)
2	71125	101	10.75	--	--	--	--	50

Remarks:

Checked by: RWoj
 George S. Morrell, Supervisor

071077

Auburn Concrete - Auburn Plant

Material Type	Material	Target Wgt	Actual Wgt	Moisture %,
AGGREGATE	67 Stone	13700	13740	1.00
AGGREGATE	Sand	11040	10980	5.25
CEMENT	Cement	4045	4085	
ADMIX	Daraccel	0	0	
ADMIX	Darex II	12	11	
HAND'S ADD	ADVA	121	121	
WATER	COLD WATER	154	157	
ADMIX	ADVA 140	160	160	
HAND'S ADD	DCI-S	0	0	

071076

Auburn Concrete - Auburn Plant

Material Type	Material	Target Wgt	Actual Wgt	Moisture %,
AGGREGATE	67 Stone	13700	13660	1.00
AGGREGATE	Sand	11040	11100	5.25
CEMENT	Cement	4045	4025	
ADMIX	Daraccel	0	0	
ADMIX	Darex II	12	12	
HAND'S ADD	ADVA	121	121	
WATER	COLD WATER	154	157	
ADMIX	ADVA 140	160	160	
HAND'S ADD	DCI-S	0	0	