

R. W. Gillespie & Associates, Inc.

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008
200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244

LETTER OF TRANSMITTAL

Doughty & Associates, Inc.

362 U.S. Route One

Falmouth, ME 04105

Date:	October 26, 2004	Project No.:	438-05
Attention:	Mr. Phillip Doughty (pdarch@maine.rr.com)		
Re:	Concrete Testing New Jetways & Addition to Baggage Claim Portland Jetport Portland, Maine		

We are sending you attached concrete cylinder test results.

Cylinder No. (s)	Age (Days)
48686	28
48687	28

Remarks:

Copy To: Roy Williams (rsw@ci.portland.me.us)
Todd Neal, Becker Structural Engineering (Todd@beckerstructural.com)

Signed: Bertha Dawn

If enclosures are not as noted, kindly notify us at once.

R. W. GILLESPIE & ASSOCIATES, INC.

86 Industrial Park Road, Suite 4, Saco, ME 04072 207-286-8008
 200 International Drive, Suite 170, Portsmouth, NH 03801 603-427-0244

CONCRETE TEST/PLACEMENT REPORT

Project Name: New Jetways & Addition to Baggage Claim
Project No: 438-05
Weather Conditions: Sunny
Method of Placement: Rear discharge
Admixtures: --
Placement Location: 16Z to 40 + 5'E Line Z
Test Cylinder Location: 40, Line E - 5'S

Date Cylinders Cast: 27-Sep-04
Concrete Supplier: Auburn
General Contractor: Ledgewood
Design Strength: 3,000
Max Agg. Size: 3/4

OCT 26 2004

Date Report Issued:

6x12 Cylinders	4	Cast by	Peter E. Callahan	Time	
Load No.	1	Slump (in) ASTM C 143	3	Batched @	--
Ticket No.	071687	Air (°F)	78	Arrived @	--
Truck No.	--	Concrete (°F) ASTM C 1064	75	Total Time	45
Cubic Yds.	2	Air Content (%) ASTM C 231	5.5		

*Concrete sampled by ASTM C 172

Specimen Storage ASTM C 31: Field cure days: 1
 Date received: 28-Sep-04
 Condition of Cylinders: Good


Lab No.	Test Date	Avg Dia (in)	Area (in ²)	Age (Days)	Load (lbs)	Compressive Strength (psi)	Break type
48685	04-Oct-04	6.006	28.33	7	80,900	2860	4
48686	25-Oct-04	5.996	28.24	28	111,600	3950	4
48687	25-Oct-04	5.996	28.24	28	100,800	3570	4
48688	HOLD			HOLD			

*Concrete compressive strength by ASTM C 39

Types of Breaks



Cone
1




Cone & Split
2



Cone & Shear
3



Shear
4



Columnar
5

Load	Ticket Number	Truck Number	Cubic Yds	Slump (inches)	Air Temp (°F)	Conc Temp (°F)	(%) Air Content	Time (min.)

Remarks:

Checked by: Matthew J. Andry
 For George S. Morrell, Supervisor